

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
27 December 2001 (27.12.2001)

(10) International Publication Number
WO 01/98623 A1

PCT

(51) International Patent Classification⁷: **E21B 19/16**

(21) International Application Number: PCT/US01/19014

(22) International Filing Date: 12 June 2001 (12.06.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/212,359 19 June 2000 (19.06.2000) US

(71) Applicant (for all designated States except US): **SHELL OIL COMPANY** [US/US]; 910 Louisiana Street, Houston, TX 77252-2463 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **COOK, Robert,**


Lance [US/US]; 934 Caswell Court, Katy, TX 77450 (US). **HAUT, Richard, Carl** [US/US]; 502 Lakebend Drive, Sugar Land, TX 77479-5831 (US). **RING, Lev** [RU/US]; 14126 Heatherhill Place, Houston, TX 77077 (US). **GRANT, Thomas, Patrick, III** [US/US]; 23 Inwood Autumn, San Antonio, TX 78248 (US). **ZWALD, Edwin, Arnold, Jr.** [US/US]; 12625 Memorial Drive, No. 110, Houston, TX 77024 (US). **FILIPPOV, Andrei** [US/US]; 2606 Hidden Shore Drive, Katy, TX 77450 (US).

(74) Agents: **BECKER, Jeffrey, M.** et al.; Haynes and Boone, LLP, Suite 4300, 1000 Louisiana, Houston, TX 77002 (US).

(81) Designated States (national): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT,

[Continued on next page]

(54) Title: **RADIAL EXPANSION OF TUBULAR MEMBERS**



(57) Abstract: An apparatus and method for coupling a tubular member (140) to a preexisting structure (100). The tubular member (140) is anchored to the preexisting structure (100) and an expansion cone (130) is pulled through the tubular member (140) to radially expand the tubular member (140).

WO 01/98623 A1



RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA,
UG, US, UZ, VN, YU, ZA, ZW.

Published:

- with international search report
- with amended claims

(84) **Designated States (regional):** ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Date of publication of the amended claims: 4 April 2002

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

AMENDED CLAIMS

[received by the International Bureau on 4 January 2002 (04.01.02);
original claims 3-13, 15-22, 28-30, 101-104, 173-183, 185-192, 198-200 amended: original claims 1, 2, 14, 24-
27, 42-44, 51-54, 56, 70, 71, 99, 100, 120-122, 125-127, 129, 132, 144, 171, 172, 184, 194-197, 212-214, 220-
223, 225, 239 and 240 cancelled; new claims 253-270 added (51 pages)]

1 1. (DELETED)

1 2. (DELETED)

1 3. The method of claim 253, wherein the lubricating fluid has a viscosity
2 ranging from about 1 to 10,000 centipoise.

1 4. The method of claim 253, wherein the injecting includes:
2 injecting lubricating fluid into a tapered end of the expansion cone.

1 5. The method of claim 253, wherein the injecting includes:
2 injecting lubricating fluid into the area around the axial midpoint of a first
3 tapered end of the expansion cone.

1 6. The method of claim 253, wherein the injecting includes:
2 injecting lubricating fluid into a second end of the expansion cone.

1 7. The method of claim 253, wherein the injecting includes:
2 injecting lubricating fluid into a tapered first end and a second end of the
3 expansion cone.

- 1 8. The method of claim 253, wherein the injecting includes:
2 injecting lubricating fluid into an interior of the expansion cone.
- 1 9. The method of claim 253, wherein the injecting includes:
2 injecting lubricating fluid through an outer surface of the expansion cone.
- 1 10. The method of claim 253, wherein the injecting includes:
2 injecting the lubricating fluid into a plurality of discrete locations along the
3 trailing edge portion.
- 1 11. The method of claim 253, wherein the lubricating fluid comprises:
2 drilling mud.
- 1 12. The method of claim 253, wherein the lubricating fluid further includes:
2 TorqTrim III;
3 EP Mudlib; and
4 DrillIN-Slid.
- 1 13. The method of claim 253, wherein the lubricating fluid comprises:
2 TorqTrim III;
3 EP Mudlib; and
4 DrillIN-Slid.
- 1 14. (DELETED)
- 1 15. The method of claim 254, wherein lubricating the interface between the
2 expansion cone and the tubular member includes:
3 coating the interior surface of the tubular member with a first part of a
4 lubricant; and
5 applying a second part of the lubricant to the interior surface of the
6 tubular member.
- 1 16. The method of claim 254, wherein the lubricant comprises a metallic soap.

- 1 17. The method of claim 254, wherein the lubricant is selected from the group
2 consisting of C-Lube-10, C-PHOS-58-M, and C-PHOS-58-R.
- 1 18. The method of claim 254, wherein the lubricant provides a sliding friction
2 coefficient of less than about 0.20.
- 1 19. The method of claim 254, wherein the lubricant is chemically bonded to
2 the interior surfaces of the tubular members.
- 1 20. The method of claim 254, wherein the lubricant is mechanically bonded to
2 the interior surfaces of the tubular members.
- 1 21. The method of claim 254, wherein the lubricant is adhesively bonded to
2 the interior surface of the tubular members.
- 1 22. The method of claim 254, wherein the lubricant includes epoxy,
2 molybdenum disulfide, graphite, aluminum, copper, aluminosilicate and
3 polyethylenepolyamine.
- 1 23. A method of coupling a tubular member to a preexisting structure,
2 comprising:
3 positioning the tubular member and an expansion cone within the
4 preexisting structure;
5 anchoring the tubular member to the preexisting structure; and
6 axially displacing the expansion cone relative to the tubular member by
7 pulling the expansion cone through the tubular member;
8 wherein the tubular member includes:
9 an annular member, including:
10 a wall thickness that varies less than about 8 %;
11 a hoop yield strength that varies less than about 10 %;
12 imperfections of less than about 8 % of the wall thickness;
13 no failure for radial expansions of up to about 30 %; and
14 no necking of the walls of the annular member for radial expansions
15 of up to about 25%.

1 24. (DELETED)

1 25. (DELETED)

1 26. (DELETED)

1 27. (DELETED)

1 28. The method of claim 264, wherein the sealing members are positioned
2 adjacent to an end portion of the threaded connection.

1 29. The method of claim 264, wherein one of the sealing members is
2 positioned adjacent to an end portion of the threaded connection; and wherein
3 another one of the sealing members is not positioned adjacent to an end portion
4 of the threaded connection.

1 30. The method of claim 264, wherein a plurality of the sealing members are
2 positioned adjacent to an end portion of the threaded connection.

1 31. A method of coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 positioning the expandable tubular member and an expansion cone
4 within the preexisting structure;
5 anchoring the expandable tubular member to the preexisting structure;
6 and
7 axially displacing the expansion cone relative to the expandable tubular
8 member by pulling the expansion cone through the expandable
9 tubular member;
10 wherein the expandable tubular member includes a plurality of tubular
11 members having threaded portions that are coupled to one
12 another by the process of:
13 coating the threaded portions of the tubular members with a
14 sealant;
15 coupling the threaded portions of the tubular members; and
16 curing the sealant.

1 32. The method of claim 31, wherein the sealant is selected from the group
2 consisting of epoxies, thermosetting sealing compounds, curable sealing
3 compounds, and sealing compounds having polymerizable materials.

1 33. The method of claim 31, further including:
2 initially curing the sealant prior to radially expanding the tubular members;
3 and
finally curing the sealant after radially expanding the tubular members.

- 1 34. The method of claim 31, wherein the sealant can be stretched up to about
- 2 30 to 40 percent after curing without failure.

- 1 35. The method of claim 31, wherein the sealant is resistant to conventional
2 wellbore fluidic materials.
- 1 36. The method of claim 31, wherein the material properties of the sealant are
2 substantially stable for temperatures ranging from about 0 to 450 °F.
- 1 37. The method of claim 31, further including:
2 applying a primer to the threaded portions of the tubular members prior to
3 coating the threaded portions of the tubular members with the
4 sealant.
- 1 38. The method of claim 37, wherein the primer includes a curing catalyst.
- 1 39. The method of claim 37, wherein the primer is applied to the threaded
2 portion of one of the tubular members and the sealant is applied to the threaded
3 portion of the other one of the tubular members.
- 1 40. The method of claim 37, wherein the primer includes a curing catalyst.
- 1 41. A method of coupling a tubular member to a preexisting structure,
2 comprising:
3 positioning the tubular member and an expansion cone within the
4 preexisting structure;
5 anchoring the tubular member to the preexisting structure; and
6 axially displacing the expansion cone relative to the tubular member by
7 pulling the expansion cone through the expandable tubular
8 member;
9 wherein the tubular member includes:
10 a pair of rings for engaging the preexisting structure; and
11 a sealing element positioned between the rings for sealing the
12 interface between the tubular member and the preexisting
13 structure.
- 1 42. (DELETED)

1 43. (DELETED)

1 44. (DELETED)

1 45. A method of coupling a tubular member to a preexisting structure,
2 comprising:
3 positioning the expandable tubular member and an expansion cone
4 within the preexisting structure;
5 anchoring the expandable tubular member to the preexisting structure;
6 and
7 axially displacing the expansion cone relative to the expandable tubular
8 member by pulling the expansion cone through the expandable
9 tubular member;
10 wherein the tubular member includes:
11 a first preexpanded portion;
12 an intermediate portion coupled to the first preexpanded portion
13 including a sealing element; and
14 a second preexpanded portion coupled to the intermediate
15 portion.

1 46. A method of coupling a tubular member to a preexisting structure,
2 comprising:
3 positioning the expandable tubular member and an expansion cone
4 within the preexisting structure;
5 anchoring the expandable tubular member to the preexisting structure;
6 and
7 axially displacing the expansion cone relative to the expandable tubular
8 member by pulling the expansion cone through the expandable
9 tubular member by applying an axial force to the expansion cone;
10 wherein the axial force includes:
11 a substantially constant axial force; and

12 an increased axial force.

1 47. The method of claim 46, wherein the increased axial force is provided on a
2 periodic basis.

1 48. The method of claim 46, wherein the increased axial force is provided on a
2 random basis.

1 49. The method of claim 46, wherein the ratio of the increased axial force to
2 the substantially constant axial force ranges from about 5 to 40 %.

1 51. (DELETED)

1 52. (DELETED)

1 53. (DELETED)

1 54. (DELETED)

1 55. A method of coupling a tubular member to a preexisting structure,
2 comprising:
3 positioning the tubular member and an expansion cone within the
4 preexisting structure;
5 anchoring the tubular member to the preexisting structure by heating a
6 portion of the tubular member; and
7 axially displacing the expansion cone relative to the tubular member by
8 pulling the expansion cone through the tubular member.

1 56. (DELETED)

1 57. A method of coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 positioning the tubular member and an expansion cone within the
4 preexisting structure;
5 explosively anchoring the tubular member to the preexisting structure; and
6 axially displacing the expansion cone relative to the tubular member.

- 1 58. A method of coupling an expandable tubular to a preexisting structure,
2 comprising:
3 fixing the position of an expansion cone within the preexisting structure;
4 driving the expandable tubular member onto the expansion cone in a first
5 direction; and
6 axially displacing the expansion cone in a second direction relative to the
7 expandable tubular member;
8 wherein the first and second directions are different.
- 1 59. A method of coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 placing the expandable tubular, an expansion cone, and a resilient
4 anchor within the preexisting structure;
5 releasing the resilient anchor; and
6 axially displacing the expansion cone within the expandable tubular
7 member.
- 1 60. A method of coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 placing the expandable tubular member, an expansion cone, and an
4 anchor into the preexisting structure;
5 anchoring the expandable tubular member to the preexisting structure by:
6 pivoting one or more engagement elements; and
7 axially displacing the expansion cone.
- 1 61. The method of claim 60, wherein pivoting the engagement elements
2 includes:
3 actuating the engagement elements.
- 1 62. The method of claim 60, wherein pivoting the engagement elements
2 includes:
3 placing a quantity of a fluidic material onto the engagement elements.

1 63. The method of claim 60, wherein pivoting the engagement elements
2 includes:
3 displacing the expandable tubular member.

1 64. A method of coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 placing the expandable tubular member and an expansion cone into the
4 preexisting structure;
5 placing a quantity of a fluidic material onto the expandable tubular
6 member to anchor the expandable tubular member to the
7 preexisting structure; and
8 axially displacing the expansion cone.

1 65. The method of claim 64, wherein the fluidic material comprises a barite
2 plug.

1 66. The method of claim 64, wherein the fluidic material comprises a flex plug.

1 67. A method of coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 positioning the expandable tubular member and an expansion cone into
4 the preexisting structure;
5 anchoring the expandable tubular member to the preexisting structure by
6 injecting a quantity of a hardenable fluidic material into the
7 preexisting structure;
8 at least partially curing the hardenable fluidic sealing material; and
9 axially displacing the expansion cone.

1 68. A method of coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 placing the expandable tubular member and an expansion cone within
4 the preexisting structure; and
5 applying an axial force to the expandable tubular member in a
6 downward direction.

1 69. A method of coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 placing the expandable tubular member and an expansion cone within
4 the preexisting structure;
5 injecting a quantity of a first fluidic material having a first density into the
6 region of the preexisting structure outside of the expandable
7 tubular member; and
8 injecting a quantity of a second fluidic material having a second density
9 into a portion of the expandable tubular member below the
10 expansion cone;
11 wherein the second density is greater than the first density.

1 70. (DELETED)

1 71. (DELETED)

1 72. An apparatus for coupling a tubular member to a preexisting structure,
2 comprising:
3 an expandable tubular member;
4 an anchoring device adapted to couple the expandable tubular member
5 to the preexisting structure; and
6 an expansion cone movably coupled to the expandable tubular member
7 and adapted to radially expand the expandable tubular member,
8 including:
9 a housing including a tapered first end and a second end;
10 one or more grooves formed in the outer surface of the tapered first
11 end; and
12 one or more axial flow passages fluidically coupled to the grooves.

1 73. The apparatus of claim 72, wherein the grooves comprise circumferential
2 grooves.

- 1 74. The apparatus of claim 72, wherein the grooves comprise spiral grooves.
- 1 75. The apparatus of claim 72, wherein the grooves are concentrated around
2 the axial midpoint of the tapered portion of the housing.
- 1 76. The apparatus of claim 72, wherein the axial flow passages comprise axial
2 grooves.
- 1 77. The apparatus of claim 76, wherein the axial grooves are spaced apart by
2 at least about 3 inches in the circumferential direction.
- 1 78. The apparatus of claim 76, wherein the axial grooves extend from the
2 tapered first end of the body to the grooves.
- 1 79. The apparatus of claim 76, wherein the axial grooves extend from the
2 second end of the body to the grooves.
- 1 80. The apparatus of claim 76, wherein the axial grooves extend from the
2 tapered first end of the body to the second end of the body.
- 1 81. The apparatus of claim 72, wherein the axial flow passages are positioned
2 within the housing of the expansion cone.
- 1 82. The apparatus of claim 81, wherein the axial flow passages extend from
2 the tapered first end of the body to the grooves.
- 1 83. The apparatus of claim 81, wherein the axial flow passages extend from
2 the tapered first end of the body to the second end of the body.
- 1 84. The apparatus of claim 83, wherein the axial flow passages extend from
2 the second end of the body to the grooves.
- 1 85. The apparatus of claim 83, wherein one or more of the flow passages
2 include inserts having restricted flow passages.

- 3 86. The apparatus of claim 83, wherein one or more of the axial flow passages
4 include filters.
- 1 87. The apparatus of claim 72, wherein the cross sectional area of the grooves
2 is greater than the cross sectional area of the axial flow passages.
- 1 88. The apparatus of claim 72, wherein the cross-sectional area of the grooves
2 ranges from about $2 \times 10^{-4} \text{ in}^2$ to $5 \times 10^{-2} \text{ in}^2$.
- 1 89. The apparatus of claim 72, wherein the cross-sectional area of the axial
2 flow passages ranges from about $2 \times 10^{-4} \text{ in}^2$ to $5 \times 10^{-2} \text{ in}^2$.
- 1 90. The apparatus of claim 72, wherein the angle of attack of the first tapered
2 end of the body ranges from about 10 to 30 degrees.
- 1 91. The apparatus of claim 72, wherein the grooves are concentrated in a
2 trailing edge portion of the tapered first end.
- 1 92. The apparatus of claim 72, wherein the angle of inclination of the axial
2 flow passages relative to the longitudinal axis of the expansion cone is greater
3 than the angle of attack of the first tapered end.
- 1 93. The apparatus of claim 72, wherein the grooves include:
2 a flow channel having a first radius of curvature;
3 a first shoulder positioned on one side of the flow channel having a
4 second radius of curvature; and
5 a second shoulder positioned on the other side of the flow channel having
6 a third radius of curvature.
- 1 94. The apparatus of claim 93, wherein the first, second and third radii of
2 curvature are substantially equal.
- 1 95. The apparatus of claim 72, wherein the axial flow passages include:
2 a flow channel having a first radius of curvature;

3 a first shoulder positioned on one side of the flow channel having a
4 second radius of curvature; and
5 a second shoulder positioned on the other side of the flow channel having
6 a third radius of curvature.

1 96. The apparatus of claim 95, wherein the first, second and third radii of
2 curvature are substantially equal.

1 97. The apparatus of claim 95, wherein the second radius of curvature is
2 greater than the third radius of curvature.

1 98. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 an expandable tubular member;
4 an anchoring device adapted to couple the expandable tubular member
5 to the preexisting structure; and
6 an expansion cone movably coupled to the expandable tubular member
7 and adapted to radially expand the expandable tubular member;
8 wherein the expandable tubular member includes:
9 an annular member, having:
10 a wall thickness that varies less than about 8 %;
11 a hoop yield strength that varies less than about 10 %;
12 imperfections of less than about 8 % of the wall thickness;
13 no failure for radial expansions of up to about 30 %; and
14 no necking of the walls of the annular member for radial
15 expansions of up to about 25%.

1 99. (DELETED)

1 100. (DELETED)

1 101. The apparatus of claim 266, wherein the sealing members are positioned
2 adjacent to an end portion of the threaded connection.

1 102. The apparatus of claim 266, wherein one of the sealing members is
2 positioned adjacent to an end portion of the threaded connection; and wherein
3 another one of the sealing members is not positioned adjacent to an end portion
4 of the threaded connection.

1 103. The apparatus of claim 266, wherein a plurality of the sealing members are
2 positioned adjacent to an end portion of the threaded connection.

1 104. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 an expandable tubular member;
4 an anchoring device adapted to couple the expandable tubular member
5 to the preexisting structure; and
6 an expansion cone movably coupled to the expandable tubular member
7 and adapted to radially expand the expandable tubular member;
8 wherein the expandable tubular member includes:
9 a layer of a lubricant bonded to the interior surface of the tubular
10 member.

1 105. The apparatus of claim 104, wherein the lubricant comprises a metallic
2 soap.

- 1 106. The apparatus of claim 104, wherein the lubricant is selected from the
2 group consisting of C-Lube-10, C-PHOS-58-M, and C-PHOS-58-R.
- 1 107. The apparatus of claim 104, wherein the lubricant provides a sliding friction
2 coefficient of less than about 0.20.
- 1 108. The apparatus of claim 104, wherein the lubricant is chemically bonded to
2 the interior surface of the expandable tubular member.
- 1 109. The apparatus of claim 104, wherein the lubricant is mechanically bonded
2 to the interior surface of the expandable tubular member.
- 1 110. The apparatus of claim 104, wherein the lubricant is adhesively bonded to
2 the interior surface of the expandable tubular member.
- 1 111. The apparatus of claim 110, wherein the lubricant includes epoxy,
2 molybdenum disulfide, graphite, aluminum, copper, aluminosilicate and
3 polyethylenepolyamine.
- 1 112. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 an expandable tubular member;
4 an anchoring device adapted to couple the expandable tubular member
5 to the preexisting structure; and
6 an expansion cone movably coupled to the expandable tubular member
7 and adapted to radially expand the expandable tubular member;
8 wherein the expandable tubular member includes:
9 a pair of tubular members having threaded portions coupled to
10 one another; and
11 a quantity of a sealant within the threaded portions of the tubular
12 members.

- 1 113. The apparatus of claim 112, wherein the sealant is selected from the group
- 2 consisting of epoxies, thermosetting sealing compounds, curable sealing
- 3 compounds, and sealing compounds having polymerizable materials.

1 114. The apparatus of claim 112, wherein the sealant includes an initial cure
2 cycle and a final cure cycle.

1 115. The apparatus of claim 112, wherein the sealant can be stretched up to
2 about 30 to 40 percent without failure.

1 116. The apparatus of claim 112, wherein the sealant is resistant to conventional
2 wellbore fluidic materials.

1 117. The apparatus of claim 112, wherein the material properties of the sealant
2 are substantially stable for temperatures ranging from about 0 to 450 °F.

1 118. The apparatus of claim 112, wherein the threaded portions of the tubular
2 members include a primer for improving the adhesion of the sealant to the
3 threaded portions.

1 119. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 an expandable tubular member;
4 an anchoring device adapted to couple the expandable tubular member
5 to the preexisting structure; and
6 an expansion cone movably coupled to the expandable tubular member
7 and adapted to radially expand the expandable tubular member;
8 wherein the expandable tubular member includes:
9 a pair of rings for engaging the preexisting structure; and
10 a sealing element positioned between the rings for sealing the
11 interface between the tubular member and the preexisting
12 structure.

1 120. (DELETED)

1 121. (DELETED)

1 122. (DELETED)

1 123. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 an expandable tubular member;
4 an anchoring device adapted to couple the expandable tubular member
5 to the preexisting structure; and
6 an expansion cone movably coupled to the expandable tubular member
7 and adapted to radially expand the expandable tubular member;
8 wherein the expandable tubular member includes:
9 a first preexpanded portion;
10 an intermediate portion coupled to the first preexpanded portion
11 including a sealing element; and
12 a second preexpanded portion coupled to the intermediate
13 portion.

1 124. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 an expandable tubular member;
4 an anchoring device adapted to couple the expandable tubular member
5 to the preexisting structure;
6 an expansion cone movably coupled to the expandable tubular member
7 and adapted to radially expand the expandable tubular member;
8 and
9 a valveable fluid passage coupled to the anchoring device.

1 125. (DELETED)

i 126. (DELETED)

1 127. (DELETED)

1 128. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 a first support member;
4 a second support member coupled to the first support member;
5 an expansion cone coupled to the first support member;
6 an expandable tubular member coupled to the expansion cone; and
7 an explosive anchoring device coupled to the second support member
8 adapted to couple the expandable tubular member to the
9 preexisting structure.

1 129. (DELETED)

1 130. (DELETED)

1 131. (DELETED)

1 132. (DELETED)

1 133. An apparatus for coupling an expandable tubular to a preexisting
2 structure, comprising:
3 a support member;
4 an expansion cone coupled to the support member;
5 an expandable tubular member coupled to the expansion cone including
6 one or more shape memory metal inserts; and
7 a heater coupled to the support member in opposing relation to the
8 shape memory metal inserts.

1 134. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 a support member;
4 an expansion cone coupled to the support member;
5 an expandable tubular member coupled to the expandable expansion
6 cone; and
7 a resilient anchor coupled to the expandable tubular member.

1 135. The apparatus of claim 134, wherein the resilient anchor includes:
2 a resilient scroll.

1 136. The apparatus of claim 134, wherein the resilient anchor includes:
2 one or more resilient arms.

1 137. The apparatus of claim 134, wherein the resilient anchor includes:
one or more resilient radially oriented elements.

1 138. The apparatus of claim 134, wherein the resilient anchor is adapted to
2 mate with the expansion cone.

1 139. An expandable tubular member, comprising:
2 an expandable tubular body;
3 one or more resilient panels coupled to the expandable tubular body; and
4 a release member releasably coupled to the resilient panels adapted to
5 controllably release the resilient panels.

1 140. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 a support member;
4 an expansion cone coupled to the support member;
5 an expandable tubular member coupled to the expandable expansion
6 cone; and
7 an anchor coupled to the expandable tubular member, including:
8 one or more spikes pivotally coupled to the expandable tubular
9 member for engaging the preexisting structure.

1 141. The apparatus of claim 140, further including one or more corresponding
2 actuators for pivoting the spikes.

1 142. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 a support member;
4 an expansion cone coupled to the support member;
5 an expandable tubular member coupled to the expandable expansion
6 cone; and
7 an anchor coupled to the expandable tubular member, including:
8 one or more petal baskets pivotally coupled to the expandable
9 tubular member.

1 143. The apparatus of claim 142, further including one or more corresponding
2 actuators for pivoting the petal baskets.

1 144. (DELETED)

1 145. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 a support member;
4 an expansion cone;
5 an expandable tubular member coupled to the expansion cone;
6 a coupling device coupled to the support member and an end portion of
7 the expandable tubular member; and
8 a mass coupled to the end portion of the expandable tubular member;
9 wherein the weight of the mass is greater than about 50 to 100 % of the
10 yield strength of the expandable tubular member.

1 146. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 a support member including a fluid passage;
4 an expansion cone coupled to the support member;
5 an expandable tubular member coupled to the expansion cone;
6 a slip joint coupled to the expansion cone;
7 an end plate coupled to the slip joint;
8 a fluid chamber coupled to the fluid passage, the fluid chamber defined
9 by the interior portion of the expandable tubular member between
10 the expansion cone and the end plate.

1 147. A method of coupling a tubular member to a preexisting structure,
2 comprising:
3 positioning the tubular member and an expansion cone within the
4 preexisting structure;
5 axially displacing the expansion cone;
6 removing the expansion cone; and
7 applying direct radial pressure to the tubular member.

1 148. The method of claim 147, wherein axially displacing the expansion cone
2 includes:
3 pressurizing at least a portion of the interior of the tubular member.

1 149. The method of claim 147, wherein axially displacing the expansion cone
2 includes:
3 injecting a fluidic material into the tubular member.

1 150. The method of claim 147, wherein axially displacing the expansion cone
2 includes:
3 applying a tensile force to the expansion cone.

1 151. The method of claim 147, wherein axially displacing the expansion cone
2 includes:
3 displacing the expansion cone into the tubular member.

1 152. The method of claim 147, wherein axially displacing the expansion cone
2 includes:
3 displacing the expansion cone out of the tubular member.

1 153. The method of claim 147, wherein axially displacing the expansion cone
2 radially expands the tubular member by about 10% to 20%.

1 154. The method of claim 147, wherein applying direct radial pressure to the first
2 tubular member radially expands the tubular member by up to about 5%.

1 155. The method of claim 147, wherein applying direct radial pressure to the
2 tubular member includes applying a radial force at discrete locations.

1 156. The method of claim 147, wherein the preexisting structure includes a
2 wellbore casing.

1 157. The method of claim 147, wherein the preexisting structure includes a
2 pipeline.

3 158. The method of claim 147, wherein the preexisting structure includes a
4 structural support.

1 159. An apparatus, comprising:
2 a tubular member coupled to a preexisting structure;
3 wherein the tubular member is coupled to the preexisting structure by the
4 process of:
5 positioning the tubular member and an expansion cone within the
6 preexisting structure;
7 axially displacing the expansion cone;
8 removing the expansion cone; and
9 applying direct radial pressure to the tubular member.

1 160. The apparatus of claim 159, wherein axially displacing the expansion cone
2 includes:
3 pressurizing at least a portion of the interior of the tubular member.

1 161. The apparatus of claim 159, wherein axially displacing the expansion cone
2 includes:
3 injecting a fluidic material into the tubular member.

1 162. The apparatus of claim 159, wherein axially displacing the expansion cone
2 includes:
3 applying a tensile force to the expansion cone.

1 163. The apparatus of claim 159, wherein axially displacing the expansion cone
2 includes:
3 displacing the expansion cone into the tubular member.

1 164. The apparatus of claim 159, wherein axially displacing the expansion cone
2 includes:
3 displacing the expansion cone out of the tubular member.

- 1 165. The apparatus of claim 159, wherein axially displacing the expansion cone
- 2 radially expands the tubular member by about 10% to 20%.

- 1 166. The apparatus of claim 159, wherein applying direct radial pressure to the
2 tubular member radially expands the tubular member by up to about 5%.
- 1 167. The apparatus of claim 159, wherein applying direct radial pressure to the
2 tubular member includes applying a radial force at discrete locations.
- 1 168. The apparatus of claim 159, wherein the preexisting structure includes a
2 wellbore casing.
- 1 169. The apparatus of claim 159, wherein the preexisting structure includes a
2 pipeline.
- 1 170. The apparatus of claim 159, wherein the preexisting structure includes a
2 structural support.
- 1 171. (DELETED)
- 1 172. (DELETED)
- 1 173. The system of claim 268, wherein the lubricating fluid has a viscosity
2 ranging from about 1 to 10,000 centipoise.

- 1 174. The system of claim 268, wherein the injecting includes:
2 injecting lubricating fluid into a tapered end of the expansion cone.
- 1 175. The system of claim 268, wherein the means for injecting includes:
2 means for injecting lubricating fluid into the area around the axial
3 midpoint of a first tapered end of the expansion cone.
- 1 176. The system of claim 268, wherein the means for injecting includes:
2 means for injecting lubricating fluid into a second end of the expansion
3 cone.
- 1 177. The system of claim 268, wherein the means for injecting includes:
2 means for injecting lubricating fluid into a tapered first end and a second
3 end of the expansion cone.
- 1 178. The system of claim 268, wherein the means for injecting includes:
2 means for injecting lubricating fluid into an interior of the expansion cone.
- 1 179. The system of claim 268, wherein the means for injecting includes:
2 means for injecting lubricating fluid through an outer surface of the
3 expansion cone.
- 1 180. The system of claim 268, wherein the means for injecting includes:
2 means for injecting the lubricating fluid into a plurality of discrete locations
3 along the trailing edge portion.
- 1 181. The system of claim 268, wherein the lubricating fluid comprises:
2 drilling mud.
- 1 182. The system of claim 268, wherein the lubricating fluid further includes:
2 TorqTrim III;
3 EP Mudlib; and
4 DrillN-Slid.

- 1 183. The system of claim 268, wherein the lubricating fluid comprises:
- 2 TorqTrim III;
- 3 EP Mudlib; and
- 4 DrillIN-Slid.

1 184. (DELETED)

1 185. The system of claim 269, wherein the means for lubricating the interface
2 between the expansion cone and the tubular member includes:
3 means for coating the interior surface of the tubular member with a first
4 part of a lubricant; and
5 means for applying a second part of the lubricant to the interior surface of
6 the tubular member.

1 186. The system of claim 269, wherein the lubricant comprises a metallic soap.

1 187. The system of claim 269, wherein the lubricant is selected from the group
2 consisting of C-Lube-10, C-PHOS-58-M, and C-PHOS-58-R.

1 188. The system of claim 269, wherein the lubricant provides a sliding friction
2 coefficient of less than about 0.20.

1 189. The system of claim 269, wherein the lubricant is chemically bonded to the
2 interior surfaces of the tubular members.

1 190. The system of claim 269, wherein the lubricant is mechanically bonded to
2 the interior surfaces of the tubular members.

1 191. The system of claim 269, wherein the lubricant is adhesively bonded to the
2 interior surface of the tubular members.

1 192. The system of claim 269, wherein the lubricant includes epoxy,
2 molybdenum disulfide, graphite, aluminum, copper, aluminosilicate and
3 polyethylenepolyamine.

1 193. A system for coupling a tubular member to a preexisting structure,
2 comprising:
3 positioning the tubular member and an expansion cone within the
4 preexisting structure;
5 anchoring the tubular member to the preexisting structure; and
6 axially displacing the expansion cone relative to the tubular member by
7 pulling the expansion cone through the tubular member;
8 wherein the tubular member includes:
9 an annular member, including:
10 a wall thickness that varies less than about 8 %;
11 a hoop yield strength that varies less than about 10 %;
12 imperfections of less than about 8 % of the wall thickness;
13 no failure for radial expansions of up to about 30 %; and
14 no necking of the walls of the annular member for radial expansions
15 of up to about 25%.

1 194. (DELETED)

1 195. (DELETED)

1 196. (DELETED)

1 197. (DELETED)

1 198. The system of claim 270, wherein the sealing members are positioned
2 adjacent to an end portion of the threaded connection.

1 199. The system of claim 270, wherein one of the sealing members is positioned
2 adjacent to an end portion of the threaded connection; and wherein another
3 one of the sealing members is not positioned adjacent to an end portion of the
4 threaded connection.

1 200. The system of claim 270, wherein a plurality of the sealing members are
2 positioned adjacent to an end portion of the threaded connection.

1 201. A system for coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 means for positioning the expandable tubular member and an expansion
4 cone within the preexisting structure;
5 means for anchoring the expandable tubular member to the preexisting
6 structure; and
7 means for axially displacing the expansion cone relative to the
8 expandable tubular member by pulling the expansion cone
9 through the expandable tubular member;

10 wherein the expandable tubular member includes a plurality of tubular
11 members having threaded portions that are coupled to one
12 another by the process of:
13 coating the threaded portions of the tubular members with a
14 sealant;
15 coupling the threaded portions of the tubular members; and
16 curing the sealant.

1 202. The system of claim 201, wherein the sealant is selected from the group
2 consisting of epoxies, thermosetting sealing compounds, curable sealing
3 compounds, and sealing compounds having polymerizable materials.

1 203. The system of claim 201, further including:
2 means for initially curing the sealant prior to radially expanding the tubular
3 members; and
4 means for finally curing the sealant after radially expanding the tubular
members.

1 204. The system of claim 201, wherein the sealant can be stretched up to about
2 30 to 40 percent after curing without failure.

1 205. The system of claim 201, wherein the sealant is resistant to conventional
2 wellbore fluidic materials.

1 206. The system of claim 201, wherein the material properties of the sealant are
2 substantially stable for temperatures ranging from about 0 to 450 °F.

1 207. The system of claim 201, further including:
2 means for applying a primer to the threaded portions of the tubular
3 members prior to coating the threaded portions of the tubular
4 members with the sealant.

1 208. The system of claim 207, wherein the primer includes a curing catalyst.

1 209. The system of claim 207, wherein the primer is applied to the threaded
2 portion of one of the tubular members and the sealant is applied to the threaded
3 portion of the other one of the tubular members.

1 210. The system of claim 207, wherein the primer includes a curing catalyst.

1 211. A system for coupling a tubular member to a preexisting structure,
2 comprising:
3 positioning the tubular member and an expansion cone within the
4 preexisting structure;
5 anchoring the tubular member to the preexisting structure; and
6 axially displacing the expansion cone relative to the tubular member by
7 pulling the expansion cone through the expandable tubular
8 member;
9 wherein the tubular member includes:
10 a pair of rings for engaging the preexisting structure; and
11 a sealing element positioned between the rings for sealing the
12 interface between the tubular member and the preexisting
13 structure.

1 212. (DELETED)

1 213. (DELETED)

1 214. (DELETED)

1 215. A system for coupling a tubular member to a preexisting structure,
2 comprising:
3 positioning the expandable tubular member and an expansion cone
4 within the preexisting structure;
5 anchoring the expandable tubular member to the preexisting structure;
6 and
7 axially displacing the expansion cone relative to the expandable tubular
8 member by pulling the expansion cone through the expandable
9 tubular member;
10 wherein the tubular member includes:
11 a first preexpanded portion;
12 an intermediate portion coupled to the first preexpanded portion
13 including a sealing element; and
14 a second preexpanded portion coupled to the intermediate
15 portion.

1 216. A system for coupling a tubular member to a preexisting structure,
2 comprising:
3 positioning the expandable tubular member and an expansion cone
4 within the preexisting structure;
5 anchoring the expandable tubular member to the preexisting structure;
6 and
7 axially displacing the expansion cone relative to the expandable tubular
8 member by pulling the expansion cone through the expandable
9 tubular member by applying an axial force to the expansion cone;
10 wherein the axial force includes:
11 a substantially constant axial force; and
12 an increased axial force.

1 217. The system of claim 216, wherein the increased axial force is provided on a
2 periodic basis.

1 218. The system of claim 216, wherein the increased axial force is provided on a
2 random basis.

- 3 219. The system of claim 216, wherein the ratio of the increased axial force to
4 the substantially constant axial force ranges from about 5 to 40 %.

1 220. (DELETED)

1 221. (DELETED)

1 222. (DELETED)

1 223. (DELETED)

1 224. A system for coupling a tubular member to a preexisting structure,
2 comprising:
3 means for positioning the tubular member and an expansion cone within
4 the preexisting structure;
5 means for anchoring the tubular member to the preexisting structure by
6 heating a portion of the tubular member; and
7 means for axially displacing the expansion cone relative to the tubular
8 member by pulling the expansion cone through the tubular
9 member.

1 225. (DELETED)

1 226. A system for coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 means for positioning the tubular member and an expansion cone within
4 the preexisting structure;
5 means for explosively anchoring the tubular member to the preexisting
6 structure; and
7 means for axially displacing the expansion cone relative to the tubular
8 member.

1 227. A system for coupling an expandable tubular to a preexisting structure,
2 comprising:
3 means for fixing the position of an expansion cone within the preexisting
4 structure;
5 means for driving the expandable tubular member onto the expansion
6 cone in a first direction; and
7 means for axially displacing the expansion cone in a second direction
8 relative to the expandable tubular member;
9

10 wherein the first and second directions are different.

1 228. A system for coupling an expandable tubular member to a preexisting
2 structure, comprising:

3 means for placing the expandable tubular, an expansion cone, and a
4 resilient anchor within the preexisting structure;

5 means for releasing the resilient anchor; and

6 means for axially displacing the expansion cone within the expandable
7 tubular member.

1 229. A system for coupling an expandable tubular member to a preexisting
2 structure, comprising:

3 means for placing the expandable tubular member, an expansion cone,
4 and an anchor into the preexisting structure;

5 means for anchoring the expandable tubular member to the preexisting
6 structure that includes means for pivoting one or more engagement
7 elements; and

8 means for axially displacing the expansion cone.

1 230. The system of claim 229, wherein the means for pivoting the engagement
2 elements includes:

3 means for actuating the engagement elements.

1 231. The system of claim 229, wherein the means for pivoting the engagement
2 elements includes:

3 means for placing a quantity of a fluidic material onto the engagement
4 elements.

1 232. The system of claim 229, wherein the means for pivoting the engagement
2 elements includes:

3 means for displacing the expandable tubular member.

1 233. A system for coupling an expandable tubular member to a preexisting
2 structure, comprising:

3 means for placing the expandable tubular member and an expansion
4 cone into the preexisting structure;
5 means for placing a quantity of a fluidic material onto the expandable
6 tubular member to anchor the expandable tubular member to the
7 preexisting structure; and
8 means for axially displacing the expansion cone.

1 234. The system of claim 233, wherein the fluidic material comprises a barite
2 plug.

1 235. The system of claim 233, wherein the fluidic material comprises a flex plug.

1 236. A system for coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 means for positioning the expandable tubular member and an expansion
4 cone into the preexisting structure;
5 means for anchoring the expandable tubular member to the preexisting
6 structure by injecting a quantity of a hardenable fluidic material
7 into the preexisting structure;
8 means for at least partially curing the hardenable fluidic sealing material;
9 and
10 means for axially displacing the expansion cone.

1 237. A system for coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 means for placing the expandable tubular member and an expansion
4 cone within the preexisting structure; and
5 means for applying an axial force to the expandable tubular member in a
6 downward direction.

1 238. A system for coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 means for placing the expandable tubular member and an expansion
4 cone within the preexisting structure;

5 means for injecting a quantity of a first fluidic material having a first density
6 into the region of the preexisting structure outside of the
7 expandable tubular member; and
8 means for injecting a quantity of a second fluidic material having a
9 second density into a portion of the expandable tubular member
10 below the expansion cone;
11 wherein the second density is greater than the first density.

1 239. (DELETED)

1 240. (DELETED)

1 241. A system for coupling a tubular member to a preexisting structure,
2 comprising:
3 means for positioning the tubular member and an expansion cone within
4 the preexisting structure;
5 means for axially displacing the expansion cone;
6 means for removing the expansion cone; and
7 means for applying direct radial pressure to the tubular member.

1 242. The system of claim 241, wherein the means for axially displacing the
2 expansion cone includes:

3 means for pressurizing at least a portion of the interior of the tubular
4 member.

1 243. The system of claim 241, wherein the means for axially displacing the
2 expansion cone includes:
3 means for injecting a fluidic material into the tubular member.

1 244. The system of claim 241, wherein the means for axially displacing the
2 expansion cone includes:
3 means for applying a tensile force to the expansion cone.

1 245. The system of claim 241, wherein the means for axially displacing the
2 expansion cone includes:
3 means for displacing the expansion cone into the tubular member.

1 246. The system of claim 241, wherein the means for axially displacing the
2 expansion cone includes:
3 means for displacing the expansion cone out of the tubular member.

1 247. The system of claim 241, wherein the means for axially displacing the
2 expansion cone radially expands the tubular member by about 10% to 20%.

1 248. The system of claim 241, wherein the means for applying direct radial
2 pressure to the first tubular member radially expands the tubular member by up
3 to about 5%.

1 249. The system of claim 241, wherein the means for applying direct radial
2 pressure to the tubular member includes means for applying a radial force at
3 discrete locations.

1 250. The system of claim 241, wherein the preexisting structure includes a
2 wellbore casing.

- 1 251. The system of claim 241, wherein the preexisting structure includes a
- 2 pipeline.

1 252. The system of claim 241, wherein the preexisting structure includes a
2 structural support.

1 253. A method of coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 positioning the tubular member and an expansion cone within the
4 preexisting structure;
5 anchoring the tubular member to the preexisting structure;
6 axially displacing the expansion cone relative to the tubular member by
7 pulling the expansion cone through the tubular member; and
8 lubricating the interface between the expansion cone and the tubular
9 member by injecting a lubricating fluid into the trailing edge of the
10 interface between the expansion cone and the tubular member.

1 254. A method of coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 positioning the tubular member and an expansion cone within the
4 preexisting structure;
5 anchoring the tubular member to the preexisting structure;
6 axially displacing the expansion cone relative to the tubular member by
7 pulling the expansion cone through the tubular member; and
8 lubricating the interface between the expansion cone and the tubular
9 member by coating the interior surface of the tubular member with
10 a lubricant.

1 255. A method of coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 positioning the tubular member and an expansion cone within the
4 preexisting structure;
5 anchoring the tubular member to the preexisting structure;
6 axially displacing the expansion cone relative to the tubular member by
7 pulling the expansion cone through the tubular member;
8 coating the interior surface of the tubular member with a first part of a
9 lubricant; and

- 10 applying a second part of the lubricant to the interior surface of the
11 tubular member.
- 1 256. The method of claim 255, wherein the lubricant comprises a metallic soap.
- 1 257. The method of claim 255, wherein the lubricant is selected from the group
2 consisting of C-Lube-10, C-PHOS-58-M, and C-PHOS-58-R.
- 1 258. The method of claim 255, wherein the lubricant provides a sliding friction
2 coefficient of less than about 0.20.
- 1 259. The method of claim 255, wherein the lubricant is chemically bonded to
2 the interior surfaces of the tubular members.
- 1 260. The method of claim 255, wherein the lubricant is mechanically bonded to
2 the interior surfaces of the tubular members.
- 1 261. The method of claim 255, wherein the lubricant is adhesively bonded to
2 the interior surface of the tubular members.
- 1 262. The method of claim 255, wherein the lubricant includes epoxy,
2 molybdenum disulfide, graphite, aluminum, copper, aluminosilicate and
3 polyethylenepolyamine.
- 1 263. A method of coupling a tubular member to a preexisting structure,
2 comprising:
3 injecting a lubricating fluid into the preexisting structure;
4 positioning the tubular member and an expansion cone within the
5 preexisting structure;
6 anchoring the tubular member to the preexisting structure; and
7 axially displacing the expansion cone relative to the tubular member by
8 pulling the expansion cone through the tubular member;
9 wherein the lubricating fluid comprises BARO-LUB GOLD-SEAL™ brand
10 drilling mud lubricant.

1 264. A method of coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 positioning the expandable tubular member and an expansion cone
4 within the preexisting structure;
5 anchoring the expandable tubular member to the preexisting structure;
6 and
7 axially displacing the expansion cone relative to the expandable tubular
8 member by pulling the expansion cone through the expandable
9 tubular member;
10 wherein the expandable tubular member includes:
11 a first tubular member;
12 a second tubular member; and
13 a pin and box threaded connection for coupling the first tubular
14 member to the second tubular member, the threaded
15 connection including:
16 one or more sealing members for sealing the interface
17 between the first and second tubular members.

1 265. A method of coupling a tubular member to a preexisting structure,
2 comprising:
3 positioning the expandable tubular member and an expansion cone
4 within the preexisting structure;
5 anchoring the expandable tubular member to the preexisting structure;
6 and
7 axially displacing the expansion cone relative to the expandable tubular
8 member by pulling the expansion cone through the expandable
9 tubular member;
10 wherein the tubular member includes one or more slots provided at a
11 preexpanded portion of the tubular member.

1 266. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 an expandable tubular member;

4 an anchoring device adapted to couple the expandable tubular member
5 to the preexisting structure; and
6 an expansion cone movably coupled to the expandable tubular member
7 and adapted to radially expand the expandable tubular member;
8 wherein the expandable tubular member includes:
9 a first tubular member;
10 a second tubular member; and
11 a pin and box threaded connection for coupling the first tubular
12 member to the second tubular member, the threaded
13 connection including:
14 one or more sealing members for sealing the interface
15 between the first and second tubular members.

1 267. An apparatus for coupling an expandable tubular member to a
2 preexisting structure, comprising:
3 a support member;
4 an expandable expansion cone coupled to the support member; and
5 an expandable tubular member coupled to the expandable expansion
6 cone;
7 wherein the expandable tubular member includes one or more anchoring
8 devices and a slotted end portion.

1 268. A system for coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 means for positioning the tubular member and an expansion cone within
4 the preexisting structure;
5 means for anchoring the tubular member to the preexisting structure;
6 means for axially displacing the expansion cone relative to the tubular
7 member by pulling the expansion cone through the tubular
8 member; and
9 means for injecting a lubricating fluid into the trailing edge of the interface
10 between the expansion cone and the tubular member.

1 269. A system for coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 means for positioning the tubular member and an expansion cone within
4 the preexisting structure;
5 means for anchoring the tubular member to the preexisting structure;
6 means for axially displacing the expansion cone relative to the tubular
7 member by pulling the expansion cone through the tubular
8 member; and
9 means for coating the interior surface of the tubular member with a
10 lubricant.

1 270. A system for coupling an expandable tubular member to a preexisting
2 structure, comprising:
3 means for positioning the expandable tubular member and an expansion
4 cone within the preexisting structure;
5 means for anchoring the expandable tubular member to the preexisting
6 structure; and
7 means for axially displacing the expansion cone relative to the
8 expandable tubular member by pulling the expansion cone
9 through the expandable tubular member;
10 wherein the expandable tubular member includes:
11 a first tubular member;
12 a second tubular member; and
13 a pin and box threaded connection for coupling the first tubular
14 member to the second tubular member, the threaded
15 connection including:
16 one or more sealing members for sealing the interface
17 between the first and second tubular members.

(12) DEMANDE INTERNATIONALE PUBLIÉE EN VERTU DU TRAITÉ DE COOPÉRATION
EN MATIÈRE DE BREVETS (PCT)

(19) Organisation Mondiale de la Propriété
Intellectuelle
Bureau international



(43) Date de la publication internationale
3 janvier 2002 (03.01.2002)


(10) Numéro de publication internationale
PCT
WO 02/01102 A1

- (51) Classification internationale des brevets⁷ : F16L 1, rue des Noyers Prolongée, F-59990 Sebourg (FR). ROUSSIE, Gabriel [FR/FR]; 15, rue Florimond Delemer, F-59370 Mons en Baroeuil (FR). VARENNE, Emmanuel [FR/FR]; 542, rue Jean-Baptiste Martini, F-69400 Villefranche-sur-Saône (FR).
- (21) Numéro de la demande internationale : PCT/FR01/02005
- (22) Date de dépôt international : 25 juin 2001 (25.06.2001)
- (25) Langue de dépôt : français
- (26) Langue de publication : français
- (30) Données relatives à la priorité : 00/08510 30 juin 2000 (30.06.2000) FR
- (71) Déposant (pour tous les États désignés sauf US) : VALLOUREC MANNESMANN OIL & GAS FRANCE [FR/FR]; 54, rue Anatole France, F-59620 Aulnoye-Aymeries (FR).
- (74) Mandataire : SETVAL- DESOLNEUX, Jean-Paul; Division Propriété Industrielle, 130, rue de Silly, F-92100 Boulogne-Billancourt (FR).
- (81) États désignés (national) : AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) États désignés (régional) : brevet ARIPO (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), brevet eurasien (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), brevet européen (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), brevet OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

[Suite sur la page suivante]

(54) Title: TUBULAR THREADED JOINT CAPABLE OF BEING SUBJECTED TO DIAMETRAL EXPANSION

(54) Titre : JOINT FILETE TUBULAIRE APTE A SUBIR UNE EXPANSION DIAMETRALE



(57) Abstract: The invention concerns a threaded joint to be expanded, comprising a lip (5) at the end of the male element (1) and a housing for said lip on the female element (2) to make the threaded joint capable of being sealed and of having a maximum internal passage cross-section after being subjected to diametral expansion by more than 10 %, the free male end surface (9) is socketed before expansion into a partially transverse shoulder surface (10) of the female housing through the matching rebating shapes of said surfaces and the male lip (5) outer peripheral surface (7) is arranged with little play of the internal peripheral surface (8) of the female housing (6). Such a threaded joint is particularly useful for casings and tubings used in oil wells.

(57) Abrégé : Le joint fileté apte à être expansé comprend un lèvres (5) en extrémité de l'élément mâle (1) et un logement pour cette lèvres sur l'élément femelle (2). pour rendre le joint fileté apte à être étanche et à présenter une section de passage intérieur maximale après avoir subi une expansion diamétrale supérieure à 10 %, la surface d'extrémité libre mâle (9) est encastrée avant expansion dans une surface partiellement transversale d'épaulement (10) du logement femelle grâce à la forme en feuillures complémentaires de ces surfaces et la surface périphérique extérieure (7) de lèvres mâle (5) est disposée à faible jeu de la surface périphérique intérieure (8) du logement femelle (6). Un tel joint fileté est particulièrement utile pour les colonnes de tubes utilisées dans les puits d'hydrocarbures.

WO 02/01102 A1

- *relative à la qualité d'inventeur (règle 4.17.iv)) pour US seulement*

- *relative au droit du déposant de demander et d'obtenir un brevet (règle 4.17.ii) pour les désignations suivantes AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW, brevet ARIPO (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), brevet eurasien (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), brevet européen (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), brevet OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG)*
- *relative au droit du déposant de revendiquer la priorité de la demande antérieure (règle 4.17.iii) pour la désignation suivante US*

- avec rapport de recherche internationale
- avant l'expiration du délai prévu pour la modification des revendications, sera republiée si des modifications sont recues

En ce qui concerne les codes à deux lettres et autres abréviations, se référer aux "Notes explicatives relatives aux codes et abréviations" figurant au début de chaque numéro ordinaire de la Gazette du PCT.

-1-

JOINT FILETÉ TUBULAIRE APTE À SUBIR UNE EXPANSION DIAMÉTRALE

L'invention concerne un joint fileté tubulaire apte à subir une déformation plastique par expansion diamétrale et le joint obtenu après une telle expansion.

- 5 On connaît des joints filetés tubulaires réalisés entre deux tubes de grande longueur ou entre un tube de grande longueur et un manchon et utilisés notamment pour constituer des colonnes de tubes de cuvelage (« casings ») ou de production (« tubings ») pour des puits d'hydrocarbures ou pour des puits similaires tels que pour la géothermie.
- 10 Traditionnellement les puits sont forés avec des outils de différents diamètres, le haut du puits étant foré à l'aide d'un outil de gros diamètre, de l'ordre par exemple de 500 mm, alors que le fond du puits est foré avec un diamètre plus faible, de l'ordre de 150 mm. Les puits sont de ce fait cuvelés à l'aide de plusieurs colonnes
- 15 concentriques toutes suspendues depuis la surface, les tubes de plus gros diamètre s'étendant depuis la surface jusqu'à quelques centaines de mètres de profondeur et les tubes de plus petit diamètre s'étendant depuis la surface jusqu'au fond du puits. L'espace entre tubes de cuvelage et le terrain est généralement cimenté.
- 20 Lorsque le puits est entièrement foré et cuvelé, une colonne de tubes de production est descendue à l'intérieur de la colonne de tubes de cuvelage de plus faible diamètre pour notamment permettre la remontée des hydrocarbures jusqu'à la surface.
- 25 Equiper un puits conduit donc à mettre en œuvre un grand nombre de tubes de différentes dimensions et les plus minces possibles pour ne pas nécessiter de trop gros diamètres de tubes de cuvelage près de la surface.
- 30 Compte tenu des caractéristiques mécaniques exigées, les tubes de cuvelage et ceux de production sont généralement en acier traité thermiquement et ils sont assemblés les uns aux autres par joints filetés, l'épaisseur des joints filetés étant généralement plus grande que celle de la partie courante des tubes et imposant les écarts de diamètres entre colonnes concentriques.

-2-

La spécification API 5 CT de l'American Petroleum Institute définit ainsi des joints filetés tubulaires entre deux tubes de grande longueur ("integral-joint tubing", "extreme-line casing") et des assemblages filetés manchonnés comportant deux joints filetés permettant d'assembler deux tubes de grande longueur à l'aide d'un manchon.

De nombreux brevets sont venus perfectionner ces joints et assemblages filetés : par exemple les brevets FR 1.489.013, EP 0 488 912, US 4,494,777 ont visé à réaliser des joints filetés tubulaires dits supérieurs ou "premium" particulièrement étanches grâce à des portées d'étanchéité métal-métal et à des butées entre éléments mâles et femelles.

Très récemment, de nouveaux modes d'utilisation des colonnes tubulaires de puits d'hydrocarbures sont envisagés consistant à gonfler de 10 à 20 % le diamètre des tubes de la colonne à l'aide d'un boulet dont le passage est forcé à l'intérieur de la colonne : voir brevets ou demandes de brevet WO 93/25799, WO 98/00626, WO 99/06670, WO 99/35368, WO 00/61915, GB 2344606, GB 2348657.

Une telle expansion peut permettre par exemple de mettre en place une colonne de tubes de cuvelage sans avoir à cimenter l'espace entre la surface périphérique extérieure des tubes et la surface du trou foré dans le sol ou en descendant une colonne de faible encombrement par rapport au trou.

Une telle expansion peut également permettre de colmater les trous d'un tube de cuvelage ou de production percé par la corrosion ou par le frottement des tiges de forage ou de descendre dans le puits des tubes de faible encombrement qui seront expansés au diamètre souhaité une fois en place.

Mais la technique d'expansion peut surtout permettre de forer des puits de diamètre uniforme sur toute leur longueur dont le cuvelage est réalisé par une colonne de tubes tous de même diamètre, les tubes étant introduits à l'état non expansé puis étant expansés in situ au diamètre du puits.

Il est alors possible de diminuer fortement le nombre de tubes nécessaire pour équiper un puits en supprimant les tubes de plus gros diamètre et de plus forte épaisseur, donc le coût du puits. Il peut même être envisagé de forer le puits

-3-

directement avec la colonne de tubes de cuvelage qui jouerait le rôle de train de tiges de forage.

Cependant les joints filetés tubulaires de l'état de la technique tels que ceux selon le
5 brevet US 4,494,777 ne permettent pas de telles utilisations.

On constate après expansion sur ces joints :

- 10 - une absence d'étanchéité qui empêche notamment de réaliser l'expansion en poussant hydrauliquement le boulet dans la colonne ;
- 15 - une flèche de l'extrémité mâle vers l'intérieur du joint qui réduit considérablement et de manière inacceptable le diamètre intérieur opérationnel de la colonne en réalisant une saillie intérieure dans l'espace défini par le diamètre intérieur opérationnel ;
- 20 - éventuellement la rupture de la lèvre par dépassement de la capacité de déformation de certaines zones particulièrement sollicitées du fait des variations d'épaisseur tout au long des éléments mâles et femelles par rapport à l'épaisseur au corps du tube.

C'est pourquoi les documents cités plus haut concernant les techniques d'expansion ne décrivent pour les modes de réalisation des jonctions entre tubes que des joints soudés (bobines de tubes raboutés préalablement par soudage déroulés depuis la
25 surface) ou des joints frottants (« slips ») alors que les joints filetés sont par ailleurs reconnus pour leurs performances combinant résistance mécanique, étanchéité en toutes conditions de service et possibilité de démontage-remontage plusieurs fois de suite.

30 A noter que l'on connaît par les documents US 5 924 745 et WO 98/42947 des joints filetés pour assembler des tubes dits EST (expansible slotted tubings) munis de fentes longitudinales permettant l'expansion diamétrale de tubes aux fonds de puits d'hydrocarbures par passage d'un mandrin d'expansion dans ces tubes. De tels joints filetés ne visent aucune caractéristique d'étanchéité, étant donné que les tubes
35 sont munis de fentes traversant la paroi des tubes et permettent à un fluide extérieur

-4-

au tube (hydrocarbure provenant du gisement) d'entrer dans le tube pour y être remonté en surface.

On a donc cherché à réaliser un joint fileté tubulaire qui soit apte à résister à l'opération d'expansion dans le puits et qui soit étanche aux liquides voire si possible aux gaz après ladite opération d'expansion.

On a aussi cherché à ce que le joint fileté tubulaire soit simple et économique à produire.

10

On a en outre cherché à ce que le joint fileté possède de bonnes caractéristiques métallurgiques en service donc après expansion, notamment à ce qu'il présente dans cet état une limite d'élasticité suffisante, à ce qu'il soit exempt de fragilité et à ce qu'il présente de bonnes caractéristiques à la fissuration sous contrainte par H₂S.

15

Selon la présente invention, le joint fileté tubulaire apte à être expansé comprend un élément fileté mâle avec un filetage mâle extérieur en extrémité d'un premier tube et un élément fileté femelle avec un filetage femelle intérieur en extrémité d'un second tube.

20

L'élément fileté mâle comprend au-delà du filetage mâle en allant vers l'extrémité libre de l'élément une lèvre mâle non filetée ayant une surface périphérique extérieure et se termine par une surface d'extrémité mâle de forme annulaire et d'orientation partiellement transversale.

25

L'élément fileté femelle comprend un filetage femelle conjugué du filetage mâle et un logement femelle non fileté pour la lèvre mâle. Ce logement comporte une surface périphérique intérieure et une surface d'épaulement femelle de forme annulaire et d'orientation partiellement transversale reliée à la surface périphérique intérieure du

30

second tube.

Le filetage mâle est vissé dans le filetage femelle jusqu'à une position où la surface d'extrémité mâle est engagée contre la surface d'épaulement femelle.

35

Selon une caractéristique générale de l'invention rendant le joint fileté tubulaire apte à être étanche et à présenter une section de passage intérieur maximale après avoir

-5-

subi une expansion diamétrale dans le domaine des déformations plastiques, les surfaces d'extrémité mâle et d'épaulement femelle possèdent des formes complémentaires l'une de l'autre réalisant avant expansion l'encastrement de la surface d'extrémité mâle par celle d'épaulement femelle.

5

De plus, la surface périphérique extérieure de la lèvre mâle est disposée à faible jeu de la surface périphérique intérieure du logement femelle.

10 L'encastrement de la surface d'extrémité mâle dans celle d'épaulement femelle impose un moment de flexion à l'extrémité libre de la lèvre mâle lorsque la zone de pleine épaisseur du second tube situé au-delà de l'épaulement femelle est inclinée lors de l'expansion par rapport à l'axe de l'assemblage

15 L'encastrement permet de constituer sur le joint fileté à l'état expansé diamétralement une zone d'étanchéité annulaire par pression de contact métal/métal entre une partie de la surface périphérique extérieure de la lèvre mâle et une partie correspondante de la surface périphérique intérieure du logement femelle.

20 L'encastrement empêche aussi toute tendance naturelle de ladite extrémité libre à plonger vers l'intérieur de la colonne lors de l'expansion et y faire saillie intérieure en l'absence d'un tel encastrement.

Ce comportement lors de l'expansion constaté par les inventeurs de manière inattendue sera explicité dans la partie détaillée de la description.

25

Par faible jeu entre surface périphérique extérieure de lèvre mâle et surface périphérique intérieure de logement femelle, on entend des jeux mesurés perpendiculairement à ces surfaces inférieurs ou égaux à 0,3 mm.

30 L'absence d'interférence radiale sensible entre surface périphérique extérieure de lèvre mâle et surface intérieure de logement femelle due à ce jeu fait que ces surfaces périphériques ne jouent pas de rôle de portées d'étanchéité sur le joint non expansé. Les inventeurs ont en effet constaté qu'une interférence radiale de ces surfaces avant expansion du joint fileté n'était pas nécessaire pour obtenir un joint
35 étanche après expansion.

-6-

Ils ont par contre constaté qu'un espace trop important entre ces surfaces ne permet pas de réaliser leur frettage après expansion, frettage nécessaire pour obtenir un joint fileté étanche.

- 5 On connaît dans l'état de la technique le brevet US 4,611,838 qui décrit un joint fileté ayant une lèvre mâle en correspondance avec un logement femelle et présentant une surface annulaire d'extrémité mâle comportant une dent annulaire et une surface annulaire d'épaulement femelle comportant une rainure annulaire, en butée l'une contre l'autre, la lèvre mâle possédant une surface périphérique extérieure torique et
- 10 le logement femelle possédant une surface périphérique intérieure conique.

- Ces surfaces périphériques interfèrent radialement en fin de vissage pour constituer des portées d'étanchéité, le brevet US 4,611,838 visant à maximaliser l'interférence radiale de la surface périphérique torique extérieure de la lèvre mâle avec la surface
- 15 périphérique conique intérieure du logement femelle en fin de vissage (et par là même l'étanchéité du joint fileté) grâce à la forme de ces surfaces périphériques et à l'effet de support de la surface inférieure de la rainure pour la surface inférieure de la dent.

- 20 Mais la surface d'extrémité mâle selon ce brevet n'est pas totalement encastrée dans celle de l'épaulement femelle du joint fileté et ne permet donc pas de transmettre un moment de flexion à l'extrémité libre de la lèvre mâle du fait de l'espace libre entre la paroi supérieure de la languette à l'extrémité libre de celle-ci et la paroi supérieure de la rainure au fond de celle-ci.

- 25 Rien ne suggère dans ce document les effets sur les portées d'étanchéité d'une expansion diamétrale avec déformation plastique ni même que ce joint fileté puisse subir une telle expansion avec succès. L'expérience acquise par les inventeurs montre que l'étanchéité d'un joint fileté selon le document US 4,611,838 ne peut être
- 30 assurée après une telle expansion.

- Le brevet US 3,870,351 présente une configuration de lèvre et d'extrémité mâles et de logement femelle voisine de la configuration du brevet US 4,611,838, la surface d'extrémité libre mâle étant bombée convexe et portant contre une surface
- 35 d'épaulement femelle bombée concave de manière à réaliser deux jeux de portées d'étanchéité métal-métal, l'un au niveau des surfaces bombées, l'autre jeu étant

-7-

disposé sur la surface périphérique extérieure de lèvre mâle et sur la surface périphérique intérieure de logement femelle. Une telle configuration permet d'augmenter l'interférence radiale entre les portées d'étanchéité périphériques.

- 5 La demande de brevet WO 99/08034 décrit un joint fileté à filets carrés ayant une lèvre mâle en correspondance avec un logement femelle et présentant des surfaces annulaires d'extrémité mâle et d'épaulement femelle en forme de feuillures en butée et encastrées l'une dans l'autre. La surface périphérique extérieure de la lèvre mâle et la surface périphérique intérieure du logement femelle présentent des parties
- 10 cylindriques qui interfèrent radialement entre elles pour former un jeu de portées d'étanchéité périphériques en fin de vissage lorsque les feuillures mâle et femelle sont encastrées.

- Le brevet US 6047997 décrit enfin une structure de tiges de forage pour conduits
- 15 souterrains pour lesquels il n'y a pas d'exigence particulière d'étanchéité. La surface d'extrémité mâle selon ce brevet est encastrée dans une surface d'épaulement femelle mais les figures font apparaître un espace important entre la surface périphérique extérieure de la lèvre mâle et la surface périphérique intérieure du logement femelle.

- 20 Aucun de ces quatre documents cités ne présente une structure identique à celle revendiquée pour la présente invention. Aucun n'envisage non plus l'expansion diamétrale des joints filetés qu'ils décrivent ni la possibilité d'obtenir des joints filetés étanches après une telle expansion.

- 25 Préférentiellement, selon la présente invention, la surface d'extrémité mâle possède pour son encastrement dans celle d'épaulement femelle la forme d'une feuillure constituée par une surface transversale du côté dirigé vers l'intérieur du joint fileté et du côté opposé de la feuillure une languette annulaire se projetant axialement. La
- 30 surface d'épaulement femelle possède pour coopérer avec la surface d'extrémité mâle la forme d'une feuillure constituée par une surface transversale du côté dirigé vers l'intérieur du joint fileté et une rainure annulaire du côté opposé, la surface transversale de feuillure mâle coopérant avec celle de feuillure femelle et la languette annulaire coopérant avec la rainure annulaire.

35

-8-

Très préférentiellement pour la présente invention, les parois annulaires de la rainure frentent celles de la languette.

Avantageusement, en position assemblée, les surfaces transversales de feuillure du
5 côté intérieur de celle-ci sont en butée l'une contre l'autre. Alternativement elles peuvent simplement être en quasi-contact.

Préférentiellement aussi l'épaisseur radiale de la languette de la feuillure mâle est
10 sensiblement égale à celle de la surface transversale de la même feuillure.

Préférentiellement aussi la hauteur mesurée axialement de la languette de la
15 feuillure mâle est sensiblement égale à son épaisseur radiale.

Préférentiellement aussi la surface périphérique extérieure de lèvre mâle et la
15 surface périphérique intérieure de logement femelle sont des surfaces cylindriques : l'usinage de ces surfaces non interférentes est donc particulièrement aisé et peu coûteux.

Avantageusement, l'épaisseur de la lèvre mâle est comprise entre $1/3$ et $2/3$ de
20 l'épaisseur du premier tube.

Cette fourchette d'épaisseur de lèvre mâle permet d'assurer une section critique en
25 pied de filetage suffisante pour une résistance adéquate à la traction axiale du joint fileté.

Avantageusement aussi, le rapport entre la longueur et l'épaisseur de la lèvre mâle
est compris entre 1 et 4, la longueur de la lèvre mâle étant mesurée jusqu'à l'aplomb
de la surface transversale de la feuillure mâle.

30 La valeur minimale de ce rapport permet la déformation plastique de la lèvre mâle et du logement femelle lors de l'expansion ; ces déformations plastiques génèrent des surfaces portant l'une sur l'autre avec une pression de contact élevée et donc l'étanchéité du joint fileté après expansion.

-9-

La valeur maximale de ce rapport permet d'éviter un flambement non maîtrisé de la lèvre mâle, flambement qui se traduirait par la saillie de ladite lèvre à l'intérieur de la colonne de tubes.

- 5 Très avantageusement, l'élément fileté mâle présente une gorge en extrémité de filetage entre filetage et lèvre mâle. Cette gorge facilite la déformation plastique de la lèvre mâle durant l'expansion du joint fileté.

De préférence, la gorge a une profondeur sensiblement égale à la hauteur du filet
10 mâle de sorte que le fond des filets mâles aboutit en fond de gorge.

De préférence également, la gorge a une longueur comprise entre 2 et 8 fois sa profondeur. Un rapport longueur/profondeur inférieur à 2 ne permet pas à la gorge de faciliter la déformation plastique de la lèvre. Un rapport longueur/profondeur
15 supérieur à 8 se traduit par un risque important de flambement de la matière vers l'intérieur de la colonne lors de l'expansion.

L'invention peut avantageusement s'appliquer tant à des joints filetés à filetages coniques qu'à des joints filetés à filetages cylindriques à simples et/ou multiples
20 étages.

Avantageusement aussi, le premier tube et le second tube ont le même diamètre intérieur tant au niveau des éléments filetés qu'au niveau du corps des tubes, ce qui facilite les opérations d'expansion.

25

Avantageusement aussi, il en est de même pour les diamètres extérieurs.

Très avantageusement, le joint fileté est de type intégral, c'est-à-dire que chaque tube est un tube de grande longueur qui comporte un élément fileté mâle à une
30 extrémité et un élément fileté femelle à l'autre extrémité, l'élément mâle d'un tube étant vissé dans l'élément femelle d'un autre tube et ainsi de suite pour constituer une colonne.

La présente invention vise ainsi à protéger un joint fileté étanche résultant de
35 l'expansion diamétrale dans le domaine des déformations plastiques d'un joint fileté tel qu'exposé ci-dessus.

Préférentiellement, l'expansion diamétrale mise en œuvre est supérieure à 10 %.

La présente invention vise aussi à protéger les joints filetés exposés ci-dessus à l'état non expansé ou expansé dont les éléments filetés sont réalisés en acier
5 comprenant des éléments avides d'azote rendant l'acier non sensible au vieillissement par écrouissage. L'acier est en outre traité thermiquement pour maximiser ses caractéristiques d'allongement réparti. Il en résulte de bonnes caractéristiques d'emploi.

10 La présente invention vise encore à protéger un procédé de réalisation d'un joint fileté tubulaire étanche.

Selon ce procédé, on part d'un joint fileté tubulaire selon l'invention exposée ci-avant dît « joint fileté tubulaire initial » pour lequel aucune caractéristique d'étanchéité n'est
15 exigée et on fait subir à ce joint fileté initial une expansion diamétrale dans le domaine des déformations plastiques à l'aide d'un boulet d'expansion de diamètre supérieur au diamètre intérieur des tubes du joint fileté initial, le boulet d'expansion étant déplacé axialement dans le joint fileté initial. La lèvre mâle et le logement femelle sont dimensionnés pour que la lèvre mâle et le logement femelle subissent
20 d'abord ensemble lors du passage du boulet une déformation plastique de flexion alors que seul le logement femelle subit ensuite une déformation plastique en sens inverse de redressement, ce qui vient fretter en final la lèvre mâle par le logement femelle.

25 Préférentiellement, la flexion de la lèvre mâle est délimitée par la présence d'une gorge à l'extrémité de la lèvre mâle du côté du filetage mâle.

Préférentiellement encore, le joint fileté tubulaire mis en œuvre est du type intégral et le boulet d'expansion est déplacé de l'élément fileté mâle vers l'élément fileté
30 femelle.

Les figures ci-après illustrent de manière non limitative des modes de réalisation de l'invention.

35 La figure 1 représente un joint fileté selon l'invention avant expansion diamétrale.

La figure 2 représente l'élément mâle du joint fileté de la figure 1.

La figure 3 représente l'élément femelle du joint fileté de la figure 1.

- 5 Les figures 4 à 7 représentent le joint fileté selon l'invention à diverses étapes du processus d'expansion.

La figure 4 représente la phase d'expansion du joint fileté.

- 10 La figure 5 représente la phase de flexion.

La figure 6 représente la phase de redressement.

La figure 7 représente l'état final du joint fileté ayant subi le processus d'expansion.

15

La figure 8 représente un détail de la figure 2 au niveau de l'extrémité libre mâle.

La figure 9 représente un détail de la figure 3 au niveau du logement femelle.

- 20 La figure 10 représente un détail de la figure 1.

- La figure 1 représente un joint fileté selon l'invention comprenant un élément fileté mâle 1 disposé en extrémité d'un premier tube 11, élément mâle qui est vissé en butée dans un élément fileté femelle 2 disposé en extrémité d'un second tube 12. Le
- 25 diamètre intérieur de l'élément fileté mâle est égal au diamètre intérieur DI des tubes 11, 12. Le diamètre extérieur de l'élément fileté femelle est en outre dans le cas présent égal au diamètre extérieur DE des tubes 11, 12 mais il peut en être autrement.

- 30 Le joint fileté est représenté sur la figure 1 à l'état simplement vissé en butée avant toute opération d'expansion diamétrale.

Le second tube 12 tel que représenté est un tube de grande longueur mais pourrait très bien être, de manière non représentée, un manchon muni de l'élément femelle 2

-12-

et d'un second élément femelle symétrique de ce dernier vissé à un élément mâle situé en extrémité d'un autre tube de grande longueur.

L'élément mâle 1 est représenté seul à la figure 2.

5

Il comprend un filetage mâle 3, conique à filets trapézoïdaux, et se prolonge vers son extrémité libre par une partie non filetée constituée par une gorge 21 et par une lèvre 5 et se termine par une surface annulaire d'extrémité mâle 9.

10 La gorge 21 possède une forme en U peu profond.

Elle démarre immédiatement au-delà du filetage et sa profondeur h_g est égale à la hauteur des filets du filetage 3. De la sorte le fond de la gorge arrive au pied du premier filet du filetage.

15

La largeur de la gorge l_g est sensiblement égale à 4 fois sa profondeur h_g .

La lèvre 5 présente :

20 a) une surface périphérique extérieure 7 de forme cylindrique,

b) une surface périphérique intérieure 19 qui correspond à la zone d'extrémité de la surface périphérique intérieure cylindrique du premier tube 11,

25 La lèvre 5 possède donc une épaisseur e_l uniforme sensiblement égale à la moitié de l'épaisseur e_t du tube 11. Elle possède une longueur l_l mesurée depuis l'extrémité de la gorge jusqu'à l'aplomb de la surface 15 (définie plus bas) sensiblement égale à 3 fois l'épaisseur de lèvre e_l .

30 La surface d'extrémité mâle 9 forme une feuillure représentée en détail à la figure 8. Cette feuillure est constituée d'une surface transversale annulaire mâle 15 et d'une languette 13 annulaire se projetant axialement. La surface transversale mâle 15 est située du côté de la feuillure dirigé vers l'intérieur du joint fileté.

35 Les parois 17, 25 de la languette 13 ne sont pas rigoureusement parallèles mais convergent légèrement vers l'extrémité libre de la languette ; ces parois sont donc

-13-

portées par des surfaces légèrement coniques coaxiales avec l'axe de l'assemblage et dont le demi-angle au sommet vaut 1 à 2 degrés.

5 L'épaisseur radiale (ed) de la languette 13 est sensiblement identique à celle de la surface transversale 15 tandis que la hauteur de la languette (hd) (ou projection axiale de celle-ci) est sensiblement égale à l'épaisseur radiale (ed) de cette même languette.

L'élément femelle 2 est représenté seul à la figure 3.

10

Il comprend un filetage femelle 4 à filets trapézoïdaux conjugué du filetage mâle 3 et une partie non filetée 6 située du côté opposé à l'extrémité libre de l'élément femelle par rapport au filetage femelle 4. Cette partie non filetée 6 forme un logement pour correspondre et coopérer avec la lèvre 5 de l'élément mâle 1.

15

Le logement femelle 6 présente une surface périphérique intérieure de logement 8 de forme cylindrique reliée d'un côté au filetage femelle 4 et de l'autre côté via un épaulement femelle 10 à la surface périphérique intérieure cylindrique 20 du second tube 12.

20

Le diamètre de la surface périphérique du logement 8 est très légèrement supérieur au diamètre de la surface périphérique extérieure 7 de la lèvre mâle 5 de sorte que les surfaces 7 et 8 peuvent coulisser l'une dans l'autre à faible jeu lors du vissage de l'élément mâle dans l'élément femelle, par exemple avec un jeu de 0,2 mm.

25

L'épaulement femelle (voir figure 9) présente une surface annulaire d'épaulement 10 qui est disposée de manière sensiblement correspondante et possède une forme sensiblement correspondante à celle d'extrémité mâle 9. La surface 10 forme une feuillure constituée d'une surface annulaire transversale femelle 16 et d'une rainure annulaire 14.

30

La surface transversale femelle 16 est située du côté de la feuillure dirigé vers l'intérieur du joint fileté.

35

La rainure 14 possède une profondeur axiale (Pr) légèrement supérieure à la hauteur de la languette 13 de sorte que, en position assemblée, les surfaces transversales

-14-

annulaires mâles et femelles 15, 16 sont en butée l'une contre l'autre tandis que l'extrémité de la languette 13 n'est pas en appui contre le fond de la rainure 14 (voir figure 10).

- 5 Les parois 18, 26 de la rainure 14 ne sont pas rigoureusement parallèles mais convergent légèrement vers le fond de la rainure ; ces parois sont donc portées par des surfaces légèrement coniques coaxiales avec l'axe de l'assemblage et dont le demi-angle au sommet vaut 1 à 2 degrés comme le demi-angle au sommet des parois 17, 25 de languette 13.

10

La largeur radiale (l_r) de la rainure n'est donc pas rigoureusement constante sur toute la profondeur de la rainure ; elle est adaptée pour que les parois périphériques de la languette 13 arrivent en contact avec les parois correspondantes de la rainure 14 un peu avant la position d'assemblage.

15

Ceci permet d'assurer à la fois le faible jeu requis entre les surfaces périphériques cylindriques de lèvres 7 et de logement 8 et le frottement de la languette 13 par la rainure 14. Ce frottement et la mise en butée des surfaces transversales 15, 16 constituent un mode préférentiel d'assurer l'encastrement de la surface d'extrémité

20

mâle 9 par celle d'épaulement femelle 10.

- Les figures 4 à 7 explicitent les phénomènes de déformation qui se produisent lorsque l'on réalise au moyen d'un boulet une expansion diamétrale de l'ordre de 15 % sur des tubes assemblés par les joints filetés qui viennent d'être décrits et qui
- 25 permettent d'obtenir en final un joint expansé étanche.

Une telle déformation effectuée sur des matériaux métalliques conduit à des déformations plastiques du métal.

- 30 On passe ainsi par exemple d'un diamètre extérieur de 139,7 mm (5" 1/2) sur le deuxième tube 12 en amont de l'expansion et par conséquent dans la partie non encore déformée à un diamètre extérieur de 157,5 mm (6,2") sur le premier tube 11 expansé (à l'aplomb ou en aval du cône de sortie 33 du boulet). Il faut de ce fait utiliser pour les tubes un métal qui accepte de telles déformations plastiques.

-15-

Les déformations plastiques générées augmentent la limite d'élasticité des produits : un tube possédant initialement une limite d'élasticité de 310 MPa (45 KSI) voit ainsi celle-ci augmenter à 380 MPa (55 KSI) après déformation.

- 5 L'expansion diamétrale est réalisée de manière connue à l'aide d'un boulet 30 (figure 4) de diamètre maximal adéquat dont on force le passage dans les tubes soit en le tirant à l'aide de tiges de forage soit en le poussant par exemple par une pression hydraulique.
- 10 Le boulet a par exemple une forme biconique avec un cône d'entrée 31 sur lequel se fait l'expansion, une partie cylindrique médiane 32 et une partie conique de sortie 33. Toutes les surfaces des parties de boulet sont raccordées entre elles par des rayons de raccordement adaptés.
- 15 La demande de brevet WO 93/25800 divulgue notamment des angles de cônes d'entrée particulièrement adaptés à l'expansion diamétrale de tubes dits EST pour l'exploitation de puits d'hydrocarbures.

- Les tubes 11, 12 ayant une section constante leurs extrémités ne posent pas de
- 20 problème particulier lors du passage du boulet pourvu que la capacité de déformation du métal dont ils sont faits soit suffisante.

- Les problèmes à résoudre viennent du fait que les éléments filetés en extrémité des tubes ont des épaisseurs plus faibles que celles au corps des tubes et tendent à se
- 25 déformer de manière différente entre les parties mâles et les parties femelles correspondantes.

- Ces déformations différentes, si elles sont maîtrisées en utilisant le joint fileté selon l'invention, permettent de réaliser un joint fileté étanche après expansion diamétrale
- 30 ne présentant pas de relief local rédhibitoire à l'intérieur de la surface périphérique intérieure des tubes.

Le processus d'expansion du joint fileté peut être décomposé en 4 phases qui font l'objet des figures 4 à 7.

-16-

Bien que l'opération d'expansion puisse tout à fait être effectuée dans le sens contraire et conduire à des résultats adéquats, on a représenté le mode préféré de déformation dans lequel le boulet se déplace de l'élément mâle 1 du premier tube 11 vers l'élément femelle 2 du second tube 12.

5

a) Phase d'expansion sur le cône du boulet

La figure 4 montre le joint fileté au cours de cette phase.

- 10 L'expansion est réalisée par le cône d'entrée 31 du boulet 30 et la figure 4 montre les filetages mâles 3 et femelles 4 en cours d'expansion diamétrale.

Sur la figure 4, le cône d'entrée 31 du boulet 30 amorce la déformation de la lèvre mâle et de la zone de logement correspondante femelle en les pliant pour les incliner
15 par rapport à l'axe de l'assemblage.

Au cours de cette phase d'expansion, les efforts de réaction au passage du boulet 30 sont progressivement transférés du premier tube 11 vers le deuxième tube 12.

20

Du fait de ces efforts de réaction, la lèvre mâle 5 est comprimée axialement au cours de cette phase d'expansion par la surface annulaire d'épaulement femelle 10.

La fin de la phase d'expansion correspond à l'arrivée de l'extrémité libre de l'élément
25 mâle à la fin du cône d'entrée 31 du boulet.

b) Phase de flexion

Au cours de cette phase, la lèvre mâle est située au niveau de la partie centrale 32
30 du boulet : voir figure 5.

i) lèvre mâle

La lèvre mâle 5 est soumise à chacune de ses deux extrémités à des moments de
35 flexion de sens opposés.

-17-

La surface d'extrémité mâle 9 est en effet encastrée dans la surface d'épaulement femelle 10 du fait des feuillures avec appuis 15, 16 et système freinant languette 13/rainure 14.

- 5 L'encastrement des feuillures oblige la zone d'extrémité libre de la lèvre mâle 5 à suivre l'inclinaison de la zone 22 de pleine épaisseur de l'élément femelle au-delà de l'épaulement, zone 22 qui est encore en cours d'expansion sur le cône d'entrée 31 du boulet et crée donc un moment de flexion à ce niveau.
- 10 L'autre extrémité de la lèvre, du côté filetage mâle 3, n'est plus supportée et impose au contraire à la lèvre un moment de flexion de plus opposé par rapport à celui en extrémité libre de lèvre.

- Les moments de flexion de signe opposé aux 2 extrémités de la lèvre mâle entraînent la courbure en banane de la lèvre mâle 5 comme sur la figure 5, la surface périphérique extérieure 7 de la lèvre 5 prenant une forme bombée convexe.
- 15

L'état de compression axiale de la lèvre mâle 5 en fin de phase d'expansion facilite sa courbure sous l'effet des mouvements de flexion.

20

La gorge 21 située entre la lèvre mâle 5 et le filetage mâle 3 joue le rôle d'une rotule plastique qui accentue la courbure de la lèvre mâle en limitant la largeur sur laquelle cette courbure peut s'effectuer.

- 25 Il faut toutefois veiller dans ce cas à ce que les contraintes de compression axiale au niveau de la lèvre mâle n'induisent pas le flambement du métal 23 sous la gorge, ce qui se traduirait par une saillie du métal sous la gorge par rapport à la surface périphérique intérieure 19.

30 ii) logement femelle

Le même phénomène de flexion se produit sur le logement femelle.

- La zone 22 de pleine épaisseur relativement rigide par rapport aux zones de lèvre relativement minces subit à son passage au niveau de la partie médiane une expansion additionnelle de sorte que le diamètre intérieur de la zone 22 devient
- 35

-18-

supérieur à celui de la zone médiane 32 du boulet. Le phénomène d'expansion additionnelle est décrit dans le document WO 93/25800.

c) Phase de redressement

5

Cette phase illustrée par la figure 6 correspond au passage de la zone 22 de pleine épaisseur femelle sur la partie médiane 32 du boulet 30.

i) logement femelle

10

La flexion générée dans la phase précédente tend à être ramenée à zéro sous l'effet de la tension et des contraintes circonférentielles, ce qui génère un état de contraintes axiales de flexion inverse par rapport à la courbure, produisant ainsi le redressement.

15

Le moment de flexion engendré par ces contraintes est proportionnel à l'épaisseur de matière en amont du redressement. Au moment d'arriver sur le tube 12 en pleine épaisseur (zone 22), le moment de flexion n'est alors pas suffisant pour redresser la zone périphérique intérieure du logement femelle qui tend à plonger alors vers l'axe du produit. Ce comportement se manifeste par une diminution locale de diamètre extérieur du tube 12.

20

ii) lèvre mâle

25 Au fur et à mesure du redressement de la partie femelle, la différence d'encombrement axial qui était générée par la flexion diminue. La lèvre mâle 5 perd donc progressivement son état de compression. Cela se poursuit avec la séparation des surfaces 15, 16 initialement en butée. Ce phénomène est renforcé par "le plongeon" de la surface périphérique intérieure 8 du logement femelle qui produit un
30 effet d'ouverture des butées 15, 16.

La déformation en banane imposée dans la phase précédente est conservée.

d) Etat final

35

La figure 7 montre l'état final du joint fileté après le passage du boulet.

L'état de contraintes circonférentielles généré par l'expansion conduit à un frettage de la surface périphérique extérieure 7 de la lèvre mâle par celle intérieure 8 du logement femelle. On peut alors parler d'auto-frettage des surfaces 7, 8 du joint fileté à l'état expansé, ce qui permet d'assurer l'étanchéité. La lèvre mâle 5 ne plonge pas
5 vers l'axe, car le déportement imposé par l'encastrement des feuilures 9, 10 a généré suffisamment de déformations plastiques.

Le retour élastique des éléments du joint fileté après passage du boulet est négligeable devant les déformations plastiques mises en jeu.

10

Le frettage radial induit une pression de contact de plusieurs dizaines de MPa, suffisante pour assurer une étanchéité aux pressions intérieures ou extérieures au joint fileté.

15 Une étanchéité est par ailleurs nécessaire lorsque l'expansion est réalisée en poussant hydrauliquement le boulet 30 sous une pression de 10 à 30 MPa, toute fuite au niveau des joints déjà expansés empêchant la pénétration du boulet plus avant dans la colonne et bloquant par conséquent le processus d'expansion.

20 On notera qu'à l'état final, il peut très bien advenir que la languette 13 ne repose plus dans la rainure 14 et notamment plus sur la paroi intérieure 18 de rainure.

Les caractéristiques objets de la revendication 1 et des revendications qui en dépendent permettent d'obtenir les résultats recherchés.

25

Une surface d'extrémité mâle 9 ne permettant pas un encastrement avec celle d'épaulement femelle 10 entraîne une plongée de cette extrémité lors de la phase de redressement qui voit la séparation des surfaces transversales 15 et 16 initialement en butée et il s'ensuit une saillie inacceptable de l'extrémité inférieure de la lèvre
30 mâle à l'intérieur de la colonne. La colonne ne permet alors plus de descendre des appareillages ou des outils d'un encombrement donné.

Le jeu trop important entre surface périphérique 7 de la lèvre mâle 5 et surface périphérique 8 du logement femelle sur le joint fileté avant expansion ne permettrait
35 pas le frettage de ces surfaces en fin d'opération d'expansion.

Une interférence radiale entre ces surfaces à l'état initial avant expansion est susceptible de gêner les déformations différentielles (courbure, redressement) entre ces surfaces lors des opérations d'expansion, déformations différentielles permettant de réaliser le fretage de ces surfaces en fin d'opération d'expansion.

5

La forme préférée en feuillure annulaire avec surfaces transversales 15, 16 et système languette 13/ rainure 14 permet d'empêcher la plongée de l'extrémité libre mâle, lors de l'expansion mais n'est qu'un exemple de mode de réalisation possible pour les surfaces encastrées 9, 10, d'autres modes étant possibles donnant le même

10

résultat.

Une lèvre mâle 5 trop mince, d'épaisseur e_1 inférieure au tiers de l'épaisseur e_1 des tubes 11, 12 ne permet pas de réaliser une butée efficace au niveau des surfaces transversales 15, 16.

15

Si l'épaisseur e_1 de la lèvre mâle 5 est au contraire supérieure aux 2/3 de l'épaisseur e_1 des tubes 11, 12, l'épaisseur du tube 12 au niveau de la zone de logement femelle entraîne une section critique de filetage femelle 4 trop faible et par conséquent une résistance insuffisante à la traction des filetages.

20

Le rapport longueur/ épaisseur de lèvre mâle 5 régit le comportement en compression et en flexion de la lèvre 5.

Une lèvre mâle 5 de longueur l_1 inférieure à son épaisseur e_1 ne permet pas la flexion suffisante de la surface périphérique 7 de la lèvre mâle 5 et/ou le redressement de la surface périphérique 8 du logement femelle.

25

Une lèvre mâle 5 de longueur l_1 supérieure à 4 fois son épaisseur e_1 peut entraîner un flambement de la lèvre mâle et une saillie intérieure de celle-ci du côté filetage.

30

Cet effet est accentué par la présence d'une gorge 21 entre filetage mâle 3 et lèvre mâle 5.

C'est pourquoi la gorge a préférentiellement une profondeur limitée à une hauteur de

35

filet et une longueur limitée par rapport à sa profondeur.

Exemple de réalisation

- 5 - Tubes de diamètre extérieur DE 139,7 mm et d'épaisseur nominale e_t 7,72 mm ($5^{1/2} \times 17,00$ lb/ft) en acier au carbone traité pour une limite d'élasticité minimale de 290 MPa (42 KSI) :

10 La composition chimique de l'acier et son traitement thermique sont adaptés pour obtenir des caractéristiques de ductilité les plus élevées possibles et plus particulièrement des caractéristiques élevées d'allongement réparti avant striction A_R lors de l'essai de traction (A_R supérieur ou égal à 15 % par exemple).

15 On choisira par exemple un acier à teneur en carbone suffisamment basse, voisine de 0,14 % (en poids), à teneur en manganèse relativement élevée, de l'ordre de 1 % et comportant une addition d'aluminium apte à fixer l'azote résiduel de l'acier.

20 Une teneur en Al de 0,035 % pour une teneur en azote de 0,010% est tout à fait convenable dans la mesure où l'acier est traité thermiquement par recuit ou par trempe suivie de revenu pour que l'addition d'Al soit effectivement à même de fixer l'azote. D'autres éléments chimiques connus pour fixer l'azote peuvent également être utilisés conjointement ou à la place de l'aluminium.

25 Une telle composition chimique qui vise à éliminer les teneurs en atomes interstitiels libres tels que ceux d'azote rend en outre l'acier insensible au phénomène néfaste de vieillissement après écrouissage qui détériore aussi les caractéristiques de ductilité.

30 L'acier peut être à l'état recuit (recuit de normalisation ou recuit de détente après travail à froid par exemple) ou dans un état structurellement équivalent.

- 35 - Joints filetés intégraux selon l'invention :
- filetages 3,4 coniques (conicité = 12,5 % sur le diamètre) à filets trapézoïdaux de hauteur radiale 1 mm et de pas axial 4 mm
 - lèvre mâle 5 de forme cylindrique

-22-

- épaisseur e_l de lèvre mâle 3,2 mm (41 % de l'épaisseur du tube)
 - longueur l_l de lèvre mâle = 11,5 mm
 - gorge 21 de profondeur h_g 1 mm et de longueur l_g 4 mm entre extrémité de filetage mâle 3 et lèvre mâle 5
- 5
- surface d'extrémité mâle 9 avec une languette 13 de hauteur axiale 1,8 mm et d'épaisseur radiale 1,8 mm
 - résistance à la traction du joint fileté ≥ 50 % de la résistance à la traction de chacun des corps de tubes 11, 12.

10 - Résultats après expansion de la colonne de tubes :

- diamètre extérieur des tubes 11, 12 = 157,5 mm (6,2")
 - épaisseur des tubes : 7,2 mm
 - limite d'élasticité des tubes ≥ 415 MPa (60 KSI)
- 15
- dureté ≤ 22 HRC (valeur maximale spécifications NACE MR 01 75)
 - passages satisfaisant aux tests suivants réalisés à l'état expansé et à l'état expansé + vieilli
- essai d'éclatement sous pression intérieure
 - essai d'effondrement sous pression extérieure ("collapse")
- 20
- essai de tenue aux chocs Charpy V
 - essai SSC de résistance à la fissuration par H_2S (SSC : "Sulfide stress cracking") selon spécification NACE TM 01-77

Nota : NACE = National association of Corrosion Engineers (USA).

- 25 La description des modes de réalisations exposés n'exclut pas que la protection accordée à la présente invention puisse s'appliquer à des modes de réalisations non exposés en détail mais couverts par la présente invention.

-23-

REVENDICATIONS

1) Joint fileté tubulaire apte à être expansé comprenant un élément fileté mâle (1) en extrémité d'un premier tube (11) et un élément fileté femelle (2) en extrémité d'un second tube (12), l'élément fileté mâle comprenant en allant vers l'extrémité libre dudit élément mâle un filetage mâle (3) et une lèvre mâle (5) qui comporte une surface périphérique extérieure (7) et se terminant transversalement par rapport à l'axe du joint fileté par une surface d'extrémité mâle (9) de forme annulaire, l'élément fileté femelle (2) comprenant un filetage femelle (4) correspondant au filetage mâle (3) et une partie non filetée (6) de logement femelle pour la lèvre mâle, ce logement femelle comprenant une surface périphérique intérieure (8) et une surface d'épaulement femelle (10), annulaire et d'orientation en partie transversale, le filetage mâle (3) étant vissé dans le filetage femelle (4) jusqu'à une position où la surface annulaire d'extrémité mâle (9) est engagée contre la surface d'épaulement femelle (10), caractérisé en ce que, pour rendre ledit joint fileté apte à être étanche et à présenter une section de passage intérieure maximale après avoir subi une expansion diamétrale dans le domaine des déformations plastiques, les surfaces annulaires d'extrémité mâle (9) et d'épaulement femelle (10) possèdent avant expansion des formes complémentaires l'une de l'autre réalisant l'encastrement de la surface d'extrémité mâle (9) par celle d'épaulement femelle (10) et en ce que la surface périphérique extérieure (7) de lèvre mâle (5) est disposée à faible jeu de la surface périphérique intérieure (8) du logement femelle (6).

2) Joint fileté tubulaire selon la revendication 1 caractérisé en ce que la surface d'extrémité mâle (9) possède la forme d'une feuillure constituée par une surface transversale (15) du côté intérieur du joint fileté et du côté opposé de la feuillure par une languette (13) annulaire se projetant axialement et en ce que la surface d'épaulement femelle (10) possède une forme de feuillure constituée par une surface transversale (16) du côté dirigé vers l'intérieur du joint fileté et par une rainure (14) annulaire du côté opposé, la surface transversale de feuillure mâle (15) coopérant avec la surface transversale de feuillure femelle (16) et la languette (13) coopérant avec la rainure (14).

3) Joint fileté tubulaire selon la revendication 2 caractérisé en ce que les parois annulaires de la languette (13) et de la rainure (14) sont disposées de manière à ce qu'en position assemblée du joint fileté, les parois annulaires (18, 26) de la rainure frentent radialement celles (17, 25) de la languette.

-24-

- 4) Joint fileté tubulaire selon la revendication 3 caractérisé en ce que les parois annulaires (17, 25) de la languette (13) sont légèrement coniques et convergent vers l'extrémité libre de la languette et en ce que les parois annulaires (18, 26) de la rainure (14) sont légèrement coniques et convergent vers le fond de la rainure,
- 5 l'inclinaison des parois de rainure étant égale à celle des parois de languette.
- 5) Joint fileté tubulaire selon l'une quelconque des revendications 2 à 4 caractérisé en ce que les surfaces transversales de feuillure mâles et femelles (15, 16) sont en butée l'une contre l'autre.
- 10 6) Joint fileté tubulaire selon l'une quelconque des revendications 2 à 5, caractérisé en ce que l'épaisseur radiale (e_d) de la languette (13) est sensiblement égale à celle de la surface transversale (15) de la feuillure mâle (9).
- 15 7) Joint fileté tubulaire selon l'une quelconque des revendications 2 à 6, caractérisé en ce que la hauteur mesurée axialement (h_d) de la languette (13) est sensiblement égale à son épaisseur radiale (e_d).
- 20 8) Joint fileté tubulaire selon l'une quelconque des revendications 1 à 7, caractérisé en ce que les surfaces périphériques extérieures (7) de lèvre mâle et intérieures (8) du logement femelle sont cylindriques.
- 9) Joint fileté tubulaire selon l'une quelconque des revendications 1 à 8 caractérisé en ce que la lèvre mâle (5) possède une épaisseur (e_l) comprise entre 1/3 et 2/3 de
- 25 l'épaisseur du premier tube (11).
- 10) Joint fileté tubulaire selon l'une quelconque des revendications 1 à 9 caractérisé en ce que la lèvre (5) possède une longueur (l_l) et une épaisseur (e_l) telles que le rapport longueur sur épaisseur de lèvre est compris entre 1 et 4.
- 30 11) Joint fileté tubulaire selon l'une quelconque des revendications 1 à 10 caractérisé en ce que l'élément mâle (1) présente une gorge (21) en extrémité du filetage mâle (3) entre filetage et lèvre mâle (5).

-25-





- 12) Joint fileté tubulaire selon la revendication 11 caractérisé en ce que la gorge (21) a une profondeur (hg) égale à la hauteur des filets mâles (3).
- 13) Joint fileté tubulaire selon la revendication 11 ou la revendication 12 caractérisé en ce que la gorge (21) a une longueur (lg) et une profondeur (hg) telles que la longueur de lèvre est comprise entre 2 et 8 fois sa profondeur.
- 14) Joint fileté tubulaire selon l'une quelconque des revendications 1 à 13 caractérisé en ce que le premier tube et le second tube (11, 12) ont le même diamètre intérieur (DI) tant au niveau des éléments filetés (1)(2) que du corps des tubes.
- 15) Joint fileté tubulaire selon la revendication 14, caractérisé en ce que le premier tube et le second tube (11, 12) ont le même diamètre extérieur (DE), tant au niveau des éléments filetés (1, 2) que du corps des tubes.
- 16) Joint fileté tubulaire selon la revendication 14 caractérisé en ce qu'il est du type intégral.
- 17) Joint fileté tubulaire étanche caractérisé en ce qu'il résulte d'un joint fileté tubulaire selon l'une quelconque des revendications 1 à 16 après une expansion diamétrale dans le domaine des déformations plastiques.
- 18) Joint fileté tubulaire étanche selon la revendication 17 caractérisé en ce que l'expansion diamétrale subie par le joint fileté tubulaire est supérieure à 10 %.
- 19) Joint fileté tubulaire selon l'une quelconque des revendications 1 à 18, caractérisé en ce que les éléments filetés (1) (2) sont réalisés en acier comprenant des éléments avides d'azote rendant l'acier insensible au vieillissement par écrouissage et en ce que l'acier est traité thermiquement pour maximaliser ses caractéristiques d'allongement réparti .
- 20) Procédé de réalisation d'un joint fileté tubulaire étanche caractérisé en ce que l'on part d'un joint fileté tubulaire selon l'une quelconque des revendications 1 à 16 dit « joint fileté tubulaire initial » pour lequel aucune caractéristique d'étanchéité n'est exigée, en ce qu'on fait subir à ce joint fileté initial une expansion diamétrale dans le domaine des déformations plastiques à l'aide d'un boulet d'expansion (30) de

-26-

diamètre supérieur au diamètre intérieur (DI) des tubes du joint fileté initial, boulet qui est déplacé axialement dans le joint fileté initial, la lèvre mâle (5) et le logement femelle (6) étant dimensionnés pour que la lèvre mâle et le logement femelle subissent d'abord ensemble lors du passage du boulet une déformation plastique de flexion alors que seul le logement femelle subit ensuite une déformation plastique en sens inverse de redressement, ce qui vient frotter en final la lèvre mâle par le logement femelle.

21) Procédé de réalisation d'un joint fileté tubulaire étanche selon la revendication 10 20, caractérisé en ce que la flexion de la lèvre mâle (5) est délimitée par la présence d'une gorge (21) à l'extrémité de la lèvre mâle du côté du filetage mâle.

22) Procédé de réalisation d'un joint fileté tubulaire étanche selon la revendication 20 ou 21, caractérisé en ce que le joint fileté tubulaire mis en œuvre est du type intégral 15 et en ce que le boulet d'expansion (30) est déplacé de l'élément fileté mâle (1) vers l'élément fileté femelle (2).



2/3

Fig 3





Fig 2



3/3




Fig 4




Fig 5




Fig 6




Fig 7

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/FR 01/02005

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 F16L15/04 F16L15/06 E21B17/042

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 F16L E21B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 99 08034 A (MARUBENI TUBULARS INC ;BANKER EDWARD O (US); KLEMENTICH ERICH F (U) 18 February 1999 (1999-02-18) cited in the application	1-10, 14-16
A	abstract; claims 1,3-5,7,8,10,20,23; figures 1,1D,2,3,9 page 9, line 10 -page 10, line 27 page 19, line 21-30 ---	17,18
X	US 4 611 838 A (HEILMANN WOLFGANG ET AL) 16 September 1986 (1986-09-16) cited in the application abstract; claim 1; figures 1-3 ---	1,2, 5-14,16, 17
X	US 3 870 351 A (MATSUKI NORIO) 11 March 1975 (1975-03-11) cited in the application abstract; claim 1; figures 1-3,7 ---	1,2, 10-14,16
-/-		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

24 October 2001

Date of mailing of the international search report

08/11/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Maukonen, K

INTERNATIONAL SEARCH REPORT

International Application No
PCT/FR 01/02005

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 1995, no. 03, 28 April 1995 (1995-04-28) & JP 06 346988 A (NIPPON STEEL CORP;OTHERS: 01), 20 December 1994 (1994-12-20) abstract page 4; figures 1,2 ----	19
P,A	WO 01 04520 A (ENVENTURE GLOBAL TECHNOLOGY LL) 18 January 2001 (2001-01-18) abstract; figures 7,7A,7B,9,10 page 13, line 12-16,22-26 page 14, line 15-18 page 15, line 4-13 -----	20

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

BEST AVAILABLE COPY

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/FR 01/02005

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9908034	A	18-02-1999	AU 8778098 A WO 9908034 A1	01-03-1999 18-02-1999
US 4611838	A	16-09-1986	DE 3207180 C1 DE 3207181 C1 DE 3207183 C1 AT 13346 T BR 8300921 A EP 0087557 A1 JP 1657543 C JP 3019434 B JP 58160687 A	28-07-1983 19-05-1983 09-06-1983 15-06-1985 16-11-1983 07-09-1983 21-04-1992 15-03-1991 24-09-1983
US 3870351	A	11-03-1975	JP 889402 C JP 48099716 A JP 52011765 B AR 218594 A1 BE 797579 A1 CA 977005 A1 CS 179983 B2 DE 2316060 A1 FR 2178948 A1 GB 1398959 A IT 981774 B NL 7304377 A ,B SU 568380 A3	30-11-1977 17-12-1973 02-04-1977 30-06-1980 16-07-1973 28-10-1975 30-12-1977 18-10-1973 16-11-1973 25-06-1975 10-10-1974 02-10-1973 05-08-1977
JP 06346988	A	20-12-1994	NONE	
WO 0104520	A	18-01-2001	AU 6953700 A WO 0104520 A1	30-01-2001 18-01-2001

Form PCT/ISA/210 (patent family annex) (July 1992)

BEST AVAILABLE COPY

RAPPORT DE RECHERCHE INTERNATIONALE

Demande internationale No
PCT/FR 01/02005

A. CLASSEMENT DE L'OBJET DE LA DEMANDE
CIB 7 F16L15/04 F16L15/06 E21B17/042

Selon la classification internationale des brevets (CIB) ou à la fois selon la classification nationale et la CIB

B. DOMAINES SUR LESQUELS LA RECHERCHE A PORTE

Documentation minimale consultée (système de classification suivi des symboles de classement)
CIB 7 F16L E21B

Documentation consultée autre que la documentation minimale dans la mesure où ces documents relèvent des domaines sur lesquels a porté la recherche

Base de données électronique consultée au cours de la recherche internationale (nom de la base de données, et si réalisable, termes de recherche utilisés)
EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERES COMME PERTINENTS

Catégorie *	Identification des documents cités, avec, le cas échéant, l'indication des passages pertinents	no. des revendications visées
X	WO 99 08034 A (MARUBENI TUBULARS INC ;BANKER EDWARD O (US); KLEMENTICH ERICH F (U) 18 février 1999 (1999-02-18) cité dans la demande	1-10, 14-16
A	abrégé; revendications 1,3-5,7,8,10,20,23; figures 1,10,2,3,9 page 9, ligne 10 -page 10, ligne 27 page 19, ligne 21-30	17,18
X	US 4 611 838 A (HEILMANN WOLFGANG ET AL) 16 septembre 1986 (1986-09-16) cité dans la demande abrégé; revendication 1; figures 1-3	1, 2, 5-14,16, 17
X	US 3 870 351 A (MATSUKI NORIO) 11 mars 1975 (1975-03-11) cité dans la demande abrégé; revendication 1; figures 1-3,7	1, 2, 10-14,16
	-/-	

☒ Voir la suite du cadre C pour la fin de la liste des documents

☒ Les documents de familles de brevets sont indiqués en annexe

* Catégories spéciales de documents cités:

- *A* document définissant l'état général de la technique, non considéré comme particulièrement pertinent
- *E* document antérieur, mais publié à la date de dépôt international ou après cette date
- *L* document pouvant jeter un doute sur une revendication de priorité ou cité pour déterminer la date de publication d'une autre citation ou pour une raison spéciale (telle qu'indiquée)
- *O* document se référant à une divulgation orale, à un usage, à une exposition ou tous autres moyens
- *P* document publié avant la date de dépôt international, mais postérieurement à la date de priorité revendiquée

- *T* document ultérieur publié après la date de dépôt international ou la date de priorité et n'appartenant pas à l'état de la technique pertinent, mais cité pour comprendre le principe ou la théorie constituant la base de l'invention
- *X* document particulièrement pertinent; l'invention revendiquée ne peut être considérée comme nouvelle ou comme impliquant une activité inventive par rapport au document considéré isolément
- *Y* document particulièrement pertinent; l'invention revendiquée ne peut être considérée comme impliquant une activité inventive lorsque le document est associé à un ou plusieurs autres documents de même nature, cette combinaison étant évidente pour une personne du métier
- *Z* document qui fait partie de la même famille de brevets

Date à laquelle la recherche internationale a été effectivement achevée

24 octobre 2001

Date d'expédition du présent rapport de recherche internationale

08/11/2001

Nom et adresse postale de l'administration chargée de la recherche internationale
Office Européen des Brevets, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Fonctionnaire autorisé

Maukonen, K

RAPPORT DE RECHERCHE INTERNATIONALE

Demande internationale No
PCT/FR 01/02005

C.(suite) DOCUMENTS CONSIDERES COMME PERTINENTS		
Catégorie	Identification des documents cités, avec, le cas échéant, l'indication des passages pertinents	no. des revendications visées
A	PATENT ABSTRACTS OF JAPAN vol. 1995, no. 03, 28 avril 1995 (1995-04-28) & JP 06 346988 A (NIPPON STEEL CORP; OTHERS: 01), 20 décembre 1994 (1994-12-20) abrégé page 4; figures 1,2 ----	19
P, A	WO 01 04520 A (ENVENTURE GLOBAL TECHNOLOGY LL) 18 janvier 2001 (2001-01-18) abrégé; figures 7, 7A, 7B, 9, 10 page 13, ligne 12-16, 22-26 page 14, ligne 15-18 page 15, ligne 4-13 -----	20

RAPPORT DE RECHERCHE INTERNATIONALE

Renseignements relatifs aux membres de familles de brevets

Demande internationale No

PCT/FR 01/02005

Document brevet cité au rapport de recherche		Date de publication	Membre(s) de la famille de brevet(s)	Date de publication
WO 9908034	A	18-02-1999	AU 8778098 A WO 9908034 A1	01-03-1999 18-02-1999
US 4611838	A	16-09-1986	DE 3207180 C1 DE 3207181 C1 DE 3207183 C1 AT 13346 T BR 8300921 A EP 0087557 A1 JP 1657543 C JP 3019434 B JP 58160687 A	28-07-1983 19-05-1983 09-06-1983 15-06-1985 16-11-1983 07-09-1983 21-04-1992 15-03-1991 24-09-1983
US 3870351	A	11-03-1975	JP 889402 C JP 48099716 A JP 52011765 B AR 218594 A1 BE 797579 A1 CA 977005 A1 CS 179983 B2 DE 2316060 A1 FR 2178948 A1 GB 1398959 A IT 981774 B NL 7304377 A , B SU 568380 A3	30-11-1977 17-12-1973 02-04-1977 30-06-1980 16-07-1973 28-10-1975 30-12-1977 18-10-1973 16-11-1973 25-06-1975 10-10-1974 02-10-1973 05-08-1977
JP 06346988	A	20-12-1994	AUCUN	
WO 0104520	A	18-01-2001	AU 6953700 A WO 0104520 A1	30-01-2001 18-01-2001

Formulaire PCT/ISA/210 (annexe familles de brevets) (juillet 1992)

BEST AVAILABLE COPY